

## Certificate of Verification

XL3t-69288

Reading No 5  
Mode Mining  
Time 2014-04-15 09:46  
Duration 121.45  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags  
INV NR GM 150  
OBJEKT TAFELGEMAELEN  
MATERIAL HOLZ METALL FASSUNG  
ANALYSESTELLE P1 RAHMEN VORDERSEITE  
MESSAUFBAU STATIV ANLIEGEND  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	0	:	N/A
La	0	:	N/A
Ba	0	:	N/A
Sb	0	:	N/A
Sn	0	:	N/A
Cd	0	:	N/A
Ag	15.955	+/-	5.295
Bal	839848.875	+/-	1178.066
Nb	0	:	N/A
Zr	0	:	N/A
Y	0	:	N/A
Sr	0	:	N/A
Rb	0	:	N/A
Th	0	:	N/A
Bi	0	:	N/A
Au	927.518	+/-	86.119
As	2213.633	+/-	74.645
Se	0	:	N/A
Pb	3899.624	+/-	72.939
Hg	11931.384	+/-	154.623
Zn	762.223	+/-	48.320
Cu	754.890	+/-	39.677
Ni	0	:	N/A
Co	0	:	N/A
Fe	77927.898	+/-	800.705
Mn	1361.405	+/-	116.841
Cr	644.440	+/-	43.025
V	101.292	+/-	55.977
Ti	500.627	+/-	292.147
Ca	16821.270	+/-	306.327
K	3715.769	+/-	236.669
Al	4790.306	+/-	614.305
P	2777.500	+/-	104.355
Si	23130.572	+/-	544.513
Cl	1172.569	+/-	29.719
S	6645.887	+/-	90.986
Mg	0	:	N/A

Supervised By: \_\_\_\_\_

## Certificate of Verification

XL3t-69288

Reading No 6  
Mode Mining  
Time 2014-04-15 09:52  
Duration 121.34  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags  
INV NR GM 150  
OBJEKT TAFELGEMAELEN  
MATERIAL HOLZ METALL FASSUNG  
ANALYSESTELLE P2 RS NIMBUS  
MESSAUFBAU STATIV ANLIEGEND  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	0	:	N/A
La	0	:	N/A
Ba	0	:	N/A
Sb	0	:	N/A
Sn	71.466	+/-	9.124
Cd	11.497	+/-	4.977
Ag	385.693	+/-	10.634
Bal	859208.688	+/-	702.739
Nb	0	:	N/A
Zr	0	:	N/A
Y	0	:	N/A
Sr	165.088	+/-	4.091
Rb	0	:	N/A
Th	0	:	N/A
Bi	0	:	N/A
Au	522.744	+/-	20.477
As	929.832	+/-	37.641
Se	0	:	N/A
Pb	2855.110	+/-	37.280
Hg	0	:	N/A
Zn	54.686	+/-	8.880
Cu	808.146	+/-	26.756
Ni	0	:	N/A
Co	0	:	N/A
Fe	1680.069	+/-	67.032
Mn	0	:	N/A
Cr	29.972	+/-	16.056
V	0	:	N/A
Ti	0	:	N/A
Ca	101073.578	+/-	736.801
K	3536.364	+/-	177.832
Al	0	:	N/A
P	7405.123	+/-	174.040
Si	7621.226	+/-	401.959
Cl	2301.538	+/-	43.856
S	11334.146	+/-	126.366
Mg	0	:	N/A

Supervised By: \_\_\_\_\_

## Certificate of Verification

XL3t-69288

Reading No 7  
Mode Mining  
Time 2014-04-15 09:55  
Duration 121.12  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags  
INV NR GM 150  
OBJEKT TAFELGEMAELEN  
MATERIAL HOLZ METALL FASSUNG  
ANALYSESTELLE P3 RS EHRENTUCH  
MESSAUFBAU STATIV ANLIEGEND  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	0	:	N/A
La	0	:	N/A
Ba	0	:	N/A
Sb	0	:	N/A
Sn	71.388	+/-	7.667
Cd	18.290	+/-	4.404
Ag	268.814	+/-	8.135
Bal	889243.500	+/-	523.408
Nb	11.795	+/-	3.442
Zr	0	:	N/A
Y	0	:	N/A
Sr	53.057	+/-	2.221
Rb	0	:	N/A
Th	0	:	N/A
Bi	0	:	N/A
Au	405.149	+/-	16.446
As	758.670	+/-	30.868
Se	0	:	N/A
Pb	2335.369	+/-	29.589
Hg	0	:	N/A
Zn	19.888	+/-	6.702
Cu	569.733	+/-	20.775
Ni	0	:	N/A
Co	0	:	N/A
Fe	1375.887	+/-	56.021
Mn	0	:	N/A
Cr	0	:	N/A
V	0	:	N/A
Ti	0	:	N/A
Ca	74135.023	+/-	540.578
K	2246.401	+/-	147.187
Al	947.542	+/-	514.709
P	6150.954	+/-	152.652
Si	8703.555	+/-	393.320
Cl	2635.523	+/-	43.872
S	9961.673	+/-	111.291
Mg	0	:	N/A

Supervised By: \_\_\_\_\_

## Certificate of Verification

XL3t-69288

Reading No 8  
Mode Mining  
Time 2014-04-15 09:59  
Duration 120.84  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags  
INV NR GM 150  
OBJEKT TAFELGEMAELEN  
MATERIAL HOLZ METALL FASSUNG  
ANALYSESTELLE P4 RS RAHMEN  
MESSAUFBAU STATIV ANLIEGEND  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	0	:	N/A
La	0	:	N/A
Ba	0	:	N/A
Sb	0	:	N/A
Sn	0	:	N/A
Cd	13.064	+/-	4.949
Ag	211.105	+/-	8.014
Bal	891284.125	+/-	706.673
Nb	0	:	N/A
Zr	0	:	N/A
Y	0	:	N/A
Sr	0	:	N/A
Rb	0	:	N/A
Th	0	:	N/A
Bi	0	:	N/A
Au	0	:	N/A
As	1673.592	+/-	60.059
Se	0	:	N/A
Pb	4766.339	+/-	68.679
Hg	6926.714	+/-	83.443
Zn	443.299	+/-	29.725
Cu	113.201	+/-	17.024
Ni	0	:	N/A
Co	0	:	N/A
Fe	618.916	+/-	59.034
Mn	0	:	N/A
Cr	0	:	N/A
V	0	:	N/A
Ti	0	:	N/A
Ca	22494.289	+/-	299.138
K	3285.292	+/-	162.702
Al	4614.438	+/-	617.488
P	11255.163	+/-	222.703
Si	18456.619	+/-	534.689
Cl	4168.099	+/-	64.473
S	29647.797	+/-	340.057
Mg	0	:	N/A

Supervised By: \_\_\_\_\_