

Messergebnisse

XL3t-69288

Reading No	12
Mode	Mining
Time	2013-07-29 12:10
Duration	120.18
Units	%
Sigma Value	2
Sequence	Final
Flags	8mm
INV.NR.	GNM Gm 133
OBJEKT	Tafelgemaelde
MATERIAL	Malschicht HOLZ
ANALYSESTELLE	P1
MESSAUFBAU	STATIV
FILTER	30 30 30 30
User Login	Stein

	%	±	Error
Ce	< LOD	:	0.021
Ba	< LOD	:	0.014
Sb	< LOD	:	0.005
Sn	< LOD	:	0.003
Cd	< LOD	:	0.002
Ag	< LOD	:	0.002
Bal	84.275	±	0.559
U	< LOD	:	0.002
Nb	< LOD	:	0.002
Zr	< LOD	:	0.002
Y	< LOD	:	0.003
Sr	0.018	±	0.001
Rb	0.005	±	0.001
Bi	< LOD	:	0.011
Pb	2.746	±	0.036
Au	< LOD	:	0.013
Se	< LOD	:	0.002
As	0.259	±	0.013
Hg	< LOD	:	0.002
Zn	< LOD	:	0.007
Cu	6.974	±	0.066
Ni	< LOD	:	0.006
Co	< LOD	:	0.009
Fe	0.220	±	0.009
Mn	0.027	±	0.005
Cr	< LOD	:	0.003
V	0.003	±	0.001
Ti	0.040	±	0.003
Ca	0.494	±	0.014
K	0.445	±	0.016
Cl	0.033	±	0.002
S	< LOD	:	0.406
P	< LOD	:	0.316
Si	4.035	±	0.117
Al	0.260	±	0.082
Mg	< LOD	:	0.905

Messergebnisse

XL3t-69288

Reading No	13
Mode	Mining
Time	2013-07-29 12:19
Duration	120.88
Units	%
Sigma Value	2
Sequence	Final
Flags	8mm
INV.NR.	GNM Gm 133
OBJEKT	Tafelgemaelde
MATERIAL	Malschicht HOLZ
ANALYSESTELLE	P2
MESSAUFBAU	STATIV
FILTER	30 30 30 30
User Login	Stein

	%	±	Error
Ce	< LOD	:	0.029
Ba	< LOD	:	0.020
Sb	< LOD	:	0.006
Sn	< LOD	:	0.003
Cd	< LOD	:	0.002
Ag	< LOD	:	0.002
BaI	77.824	±	0.894
U	< LOD	:	0.002
Nb	0.003	±	0.001
Zr	< LOD	:	0.002
Y	< LOD	:	0.006
Sr	0.017	±	0.001
Rb	0.007	±	0.001
Bi	< LOD	:	0.019
Pb	5.823	±	0.094
Au	< LOD	:	0.023
Se	< LOD	:	0.003
As	0.527	±	0.021
Hg	< LOD	:	0.003
Zn	< LOD	:	0.008
Cu	7.769	±	0.089
Ni	< LOD	:	0.008
Co	< LOD	:	0.011
Fe	0.211	±	0.011
Mn	0.034	±	0.006
Cr	< LOD	:	0.005
V	0.004	±	0.001
Ti	0.041	±	0.003
Ca	0.435	±	0.016
K	0.476	±	0.020
Cl	0.051	±	0.003
S	< LOD	:	0.701
P	< LOD	:	0.543
Si	6.242	±	0.185
Al	0.409	±	0.133
Mg	< LOD	:	1.396

Messergebnisse

XL3t-69288

Reading No	14
Mode	Mining
Time	2013-07-29 12:25
Duration	120.24
Units	%
Sigma Value	2
Sequence	Final
Flags	8mm
INV.NR.	GNM Gm 133
OBJEKT	Tafelgemaelde
MATERIAL	Malschicht HOLZ
ANALYSESTELLE	P3
MESSAUFBAU	STATIV
FILTER	30 30 30 30
User Login	Stein

	%	±	Error
Ce	< LOD	:	0.018
Ba	< LOD	:	0.012
Sb	< LOD	:	0.004
Sn	0.004	±	0.001
Cd	< LOD	:	0.002
Ag	< LOD	:	0.002
Bal	89.666	±	1.113
U	< LOD	:	0.002
Nb	< LOD	:	0.002
Zr	< LOD	:	0.002
Y	< LOD	:	0.002
Sr	0.003	±	0.001
Rb	0.003	±	0.001
Bi	< LOD	:	0.007
Pb	1.551	±	0.019
Au	0.058	±	0.012
Se	< LOD	:	0.002
As	0.409	±	0.009
Hg	1.297	±	0.014
Zn	0.027	±	0.004
Cu	0.043	±	0.003
Ni	< LOD	:	0.006
Co	< LOD	:	0.007
Fe	0.043	±	0.006
Mn	0.033	±	0.006
Cr	< LOD	:	0.004
V	< LOD	:	0.002
Ti	< LOD	:	0.003
Ca	2.987	±	0.036
K	0.255	±	0.013
Cl	0.029	±	0.005
S	< LOD	:	1.043
P	< LOD	:	0.814
Si	3.587	±	0.254
Al	< LOD	:	0.307
Mg	< LOD	:	1.712