

mRFA -Ergebnisse

XL3t-69288

Reading No 1  
Mode Mining  
Time 2019-01-15 18:08  
Duration 121.88  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags 3mm  
INV NR Gm878  
OBJEKT TAFELGEMAELENDE  
MATERIAL HOLZ METALL FASSUNG  
ANALYSESTELLE P1 NIMBUS MARIA  
MESSAUFBAU STATIV  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	122.626
La	1.000	+/-	100.919
Ba	1.000	+/-	105.626
Sb	1.000	+/-	50.962
Sn	1186.280	+/-	61.342
Cd	26.043	+/-	15.436
Ag	1.000	+/-	10.042
Bal	862732.625	+/-	1316.706
Nb	30.226	+/-	20.496
Zr	1.000	+/-	71.148
Y	1.000	+/-	16.750
Sr	167.224	+/-	9.038
Rb	1.000	+/-	34.341
Th	1.000	+/-	985.669
Bi	1.000	+/-	949.054
Au	1131.029	+/-	63.859
As	3998.655	+/-	169.096
Se	1.000	+/-	16.074
Pb	21323.020	+/-	414.530
Hg	1.000	+/-	16.064
Zn	167.103	+/-	21.772
Cu	987.494	+/-	54.993
Ni	1.000	+/-	37.970
Co	1.000	+/-	44.777
Fe	1256.763	+/-	112.103
Mn	1.000	+/-	89.117
Cr	1.000	+/-	29.496
V	1.000	+/-	18.194
Ti	1.000	+/-	87.629
Ca	71647.641	+/-	1291.973
K	574.305	+/-	158.496
Al	970.044	+/-	634.632
P	3694.667	+/-	183.373
Si	9609.914	+/-	538.473
Cl	1749.118	+/-	64.359
S	18747.805	+/-	373.536
Mg	1.000	+/-	6943.581

mRFA -Ergebnisse

XL3t-69288

Reading No 2  
Mode Mining  
Time 2019-01-15 18:12  
Duration 121.64  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags 3mm  
INV NR Gm878  
OBJEKT TAFELGEMAELEN  
MATERIAL HOLZ METALL FASSUNG  
ANALYSESTELLE P2 NIMBUS MARIA REFERENZ  
MESSAUFBAU STATIV  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	96.856
La	1.000	+/-	80.333
Ba	1.000	+/-	85.550
Sb	1.000	+/-	30.127
Sn	1.000	+/-	33.536
Cd	19.563	+/-	12.823
Ag	1.000	+/-	10.817
Bal	811342.625	+/-	1684.308
Nb	1.000	+/-	5.743
Zr	1.000	+/-	21.746
Y	1.000	+/-	3.625
Sr	211.301	+/-	8.857
Rb	1.000	+/-	11.983
Th	1.000	+/-	326.431
Bi	1.000	+/-	308.444
Au	823.561	+/-	47.070
As	97.050	+/-	26.229
Se	1.000	+/-	8.306
Pb	431.463	+/-	25.039
Hg	1.000	+/-	5.467
Zn	114.152	+/-	20.330
Cu	501.582	+/-	41.887
Ni	1.000	+/-	31.933
Co	1.000	+/-	34.954
Fe	606.312	+/-	90.986
Mn	1.000	+/-	88.155
Cr	1.000	+/-	37.479
V	1.000	+/-	24.645
Ti	1.000	+/-	119.589
Ca	170883.125	+/-	1890.258
K	776.184	+/-	175.656
Al	1.000	+/-	723.558
P	7258.839	+/-	215.037
Si	3120.751	+/-	413.233
Cl	596.592	+/-	43.584
S	3216.891	+/-	80.212
Mg	1.000	+/-	8207.396

mRFA -Ergebnisse

XL3t-69288

Reading No 3  
Mode Mining  
Time 2019-01-15 18:16  
Duration 122.18  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags 3mm  
INV NR Gm878  
OBJEKT TAFELGEMAELEN  
MATERIAL HOLZ METALL FASSUNG  
ANALYSESTELLE P3 NIMBUS MARIA  
MESSAUFBAU STATIV  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	84.643
La	1.000	+/-	69.753
Ba	1.000	+/-	73.512
Sb	1.000	+/-	26.102
Sn	68.188	+/-	20.101
Cd	18.992	+/-	11.117
Ag	8.963	+/-	7.216
Bal	830379.000	+/-	1378.775
Nb	1.000	+/-	7.859
Zr	1.000	+/-	24.138
Y	1.000	+/-	4.936
Sr	163.531	+/-	7.036
Rb	1.000	+/-	14.181
Th	1.000	+/-	342.259
Bi	1.000	+/-	342.951
Au	881.421	+/-	44.769
As	566.883	+/-	50.242
Se	1.000	+/-	8.924
Pb	2302.353	+/-	55.452
Hg	31.843	+/-	10.027
Zn	295.563	+/-	25.948
Cu	2282.922	+/-	77.266
Ni	1.000	+/-	31.255
Co	1.000	+/-	41.220
Fe	1941.811	+/-	122.675
Mn	1.000	+/-	80.659
Cr	34.336	+/-	21.181
V	1.000	+/-	22.311
Ti	1.000	+/-	124.073
Ca	134261.547	+/-	1461.033
K	1090.409	+/-	160.727
Al	1614.163	+/-	739.562
P	8819.799	+/-	228.044
Si	8291.179	+/-	524.013
Cl	613.186	+/-	43.402
S	6333.856	+/-	115.104
Mg	1.000	+/-	6351.534

mRFA -Ergebnisse

XL3t-69288

Reading No 4  
Mode Mining  
Time 2019-01-15 18:20  
Duration 120.64  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags 3mm  
INV NR Gm878  
OBJEKT TAFELGEMAELENDE  
MATERIAL HOLZ METALL FASSUNG  
ANALYSESTELLE P4 MANTEL ENGENL UZ  
MESSAUFBAU STATIV  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	180.624
La	1.000	+/-	146.994
Ba	1.000	+/-	153.685
Sb	1.000	+/-	86.328
Sn	1.000	+/-	52.902
Cd	1.000	+/-	26.349
Ag	1.000	+/-	14.355
Bal	877678.625	+/-	1494.964
Nb	45.348	+/-	34.951
Zr	1.000	+/-	113.568
Y	1.000	+/-	28.994
Sr	193.190	+/-	12.359
Rb	1.000	+/-	69.651
Th	1.000	+/-	1518.044
Bi	1.000	+/-	1254.974
Au	1.000	+/-	38.158
As	8144.359	+/-	286.327
Se	23.717	+/-	18.806
Pb	40221.930	+/-	862.344
Hg	1.000	+/-	23.115
Zn	92.099	+/-	14.851
Cu	197.268	+/-	31.580
Ni	1.000	+/-	42.902
Co	1.000	+/-	63.111
Fe	201.912	+/-	82.706
Mn	260.221	+/-	119.049
Cr	1.000	+/-	33.152
V	1.000	+/-	25.959
Ti	1.000	+/-	120.904
Ca	19722.072	+/-	518.529
K	2061.790	+/-	209.684
Al	11328.062	+/-	1149.184
P	1484.812	+/-	172.875
Si	9912.278	+/-	599.694
Cl	2462.973	+/-	91.612
S	25969.350	+/-	619.023
Mg	1.000	+/-	7821.618

mRFA -Ergebnisse

XL3t-69288

Reading No 5  
Mode Mining  
Time 2019-01-15 18:26  
Duration 120.02  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags  
INV NR Gm878  
OBJEKT TAFELGEMAELEN  
MATERIAL HOLZ METALL FASSUNG  
ANALYSESTELLE P5 MANTEL ENGEL ROTLACK  
MESSAUFBAU STATIV  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	90.241
La	1.000	+/-	41.371
Ba	1.000	+/-	44.175
Sb	51.294	+/-	16.244
Sn	12.638	+/-	8.154
Cd	17.296	+/-	6.146
Ag	4.364	+/-	3.863
Bal	899487.750	+/-	702.103
Nb	33.912	+/-	15.092
Zr	1.000	+/-	51.820
Y	1.000	+/-	12.554
Sr	132.205	+/-	5.586
Rb	1.000	+/-	30.842
Th	1.000	+/-	737.804
Bi	1.000	+/-	690.180
Au	1.000	+/-	17.843
As	5411.555	+/-	141.864
Se	1.000	+/-	15.193
Pb	23129.816	+/-	323.908
Hg	1.000	+/-	10.031
Zn	80.860	+/-	9.779
Cu	739.776	+/-	32.149
Ni	1.000	+/-	27.312
Co	1.000	+/-	24.982
Fe	751.131	+/-	63.178
Mn	311.009	+/-	70.457
Cr	1.000	+/-	26.492
V	1.000	+/-	25.762
Ti	1.000	+/-	143.931
Ca	33151.523	+/-	508.864
K	8465.939	+/-	245.218
Al	4270.214	+/-	516.666
P	1124.082	+/-	82.372
Si	14059.167	+/-	437.285
Cl	1335.412	+/-	33.820
S	7430.056	+/-	128.175
Mg	1.000	+/-	4059.401

mRFA -Ergebnisse

XL3t-69288

Reading No 6  
Mode Mining  
Time 2019-01-15 18:30  
Duration 121.70  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags  
INV NR Gm878  
OBJEKT TAFELGEMAELENDE  
MATERIAL HOLZ METALL FASSUNG  
ANALYSESTELLE P6 MANTEL MARIA  
MESSAUFBAU STATIV  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	118.760
La	1.000	+/-	54.413
Ba	1.000	+/-	57.929
Sb	53.610	+/-	20.763
Sn	1.000	+/-	9.508
Cd	1.000	+/-	9.911
Ag	1.000	+/-	5.242
Bal	865506.000	+/-	1077.652
Nb	33.414	+/-	20.555
Zr	1.000	+/-	70.486
Y	1.000	+/-	17.368
Sr	145.158	+/-	7.216
Rb	1.000	+/-	33.465
Th	1.000	+/-	989.182
Bi	1.000	+/-	905.767
Au	1.000	+/-	23.351
As	5952.142	+/-	184.626
Se	1.000	+/-	15.295
Pb	28747.969	+/-	462.089
Hg	1.000	+/-	13.048
Zn	1.000	+/-	23.253
Cu	30977.348	+/-	487.039
Ni	1.000	+/-	32.163
Co	1.000	+/-	40.400
Fe	235.476	+/-	50.403
Mn	1.000	+/-	86.808
Cr	1.000	+/-	18.765
V	1.000	+/-	18.221
Ti	117.236	+/-	88.147
Ca	8425.356	+/-	185.549
K	1528.239	+/-	127.084
Al	2661.150	+/-	519.594
P	1434.356	+/-	103.648
Si	23027.551	+/-	583.747
Cl	1300.665	+/-	34.217
S	20662.852	+/-	336.147
Mg	9191.452	+/-	5606.084

mRFA -Ergebnisse

XL3t-69288

Reading No 7  
Mode Mining  
Time 2019-01-15 18:35  
Duration 120.50  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags  
INV NR Gm878  
OBJEKT TAFELGEMAELEN  
MATERIAL HOLZ METALL FASSUNG  
ANALYSESTELLE P7 HIMMEL  
MESSAUFBAU STATIV  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	330.285
La	110.976	+/-	106.934
Ba	1.000	+/-	180.713
Sb	278.038	+/-	42.310
Sn	1.000	+/-	17.551
Cd	1.000	+/-	12.154
Ag	1.000	+/-	7.963
Bal	798552.750	+/-	2371.550
Nb	108.110	+/-	51.836
Zr	1.000	+/-	160.237
Y	1.000	+/-	41.885
Sr	136.408	+/-	12.185
Rb	1.000	+/-	84.281
Th	1.000	+/-	2202.501
Bi	1.000	+/-	1638.355
Au	1.000	+/-	47.478
As	12321.525	+/-	388.820
Se	1.000	+/-	20.103
Pb	76490.766	+/-	1489.909
Hg	1.000	+/-	27.060
Zn	64.886	+/-	31.544
Cu	31055.506	+/-	567.598
Ni	1.000	+/-	66.946
Co	50.769	+/-	42.707
Fe	1150.912	+/-	98.765
Mn	215.104	+/-	94.799
Cr	1.000	+/-	28.152
V	1.000	+/-	28.530
Ti	1.000	+/-	237.854
Ca	4598.702	+/-	165.412
K	483.398	+/-	136.438
Al	2895.012	+/-	806.114
P	2923.590	+/-	170.411
Si	13749.022	+/-	542.787
Cl	2898.150	+/-	75.513
S	37656.492	+/-	745.179
Mg	14259.936	+/-	9167.506