

mRFA -Ergebnisse

XL3t-69288

Reading No 7
 Mode Mining
 Time 2018-08-02 11:04
 Duration 121.29
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P1 ENGEL
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	113.478
La	1.000	+/-	93.124
Ba	1.000	+/-	98.603
Sb	1.000	+/-	35.930
Sn	1.000	+/-	35.800
Cd	1.000	+/-	17.773
Ag	1.000	+/-	13.807
Bal	863324.875	+/-	1321.395
Nb	30.257	+/-	19.461
Zr	1.000	+/-	67.661
Y	1.000	+/-	16.209
Sr	95.132	+/-	7.028
Rb	1.000	+/-	36.414
Th	1.000	+/-	937.200
Bi	1.000	+/-	795.594
Au	1.000	+/-	24.805
As	4148.522	+/-	167.194
Se	1.000	+/-	19.331
Pb	20320.236	+/-	389.771
Hg	1.000	+/-	14.829
Zn	285.615	+/-	24.810
Cu	2004.961	+/-	80.443
Ni	1.000	+/-	33.474
Co	1.000	+/-	35.152
Fe	565.932	+/-	85.628
Mn	1.000	+/-	89.234
Cr	1.000	+/-	26.174
V	1.000	+/-	33.889
Ti	1.000	+/-	185.384
Ca	57981.633	+/-	1067.506
K	2801.618	+/-	207.616
Al	5831.867	+/-	832.146
P	756.858	+/-	134.130
Si	23119.764	+/-	826.850
Cl	1959.583	+/-	67.963
S	16773.184	+/-	336.327
Mg	1.000	+/-	6082.904

mRFA -Ergebnisse

XL3t-69288

Reading No 8
 Mode Mining
 Time 2018-08-02 11:11
 Duration 121.83
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P2 BLAUES GEWAND KARL
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	98.414
La	1.000	+/-	79.925
Ba	1.000	+/-	83.869
Sb	1.000	+/-	28.979
Sn	53.048	+/-	21.214
Cd	1.000	+/-	18.272
Ag	1.000	+/-	7.268
Bal	911619.188	+/-	833.511
Nb	22.818	+/-	17.374
Zr	1.000	+/-	60.723
Y	1.000	+/-	14.451
Sr	82.903	+/-	6.157
Rb	1.000	+/-	34.181
Th	1.000	+/-	837.231
Bi	1.000	+/-	720.401
Au	1.000	+/-	23.145
As	3834.435	+/-	148.427
Se	1.000	+/-	14.559
Pb	18431.150	+/-	336.468
Hg	1.000	+/-	13.505
Zn	407.349	+/-	26.525
Cu	122.872	+/-	22.658
Ni	1.000	+/-	32.483
Co	283.757	+/-	52.859
Fe	845.316	+/-	90.583
Mn	1.000	+/-	80.934
Cr	26.932	+/-	25.731
V	1.000	+/-	52.597
Ti	1.000	+/-	290.634
Ca	28963.092	+/-	579.775
K	3180.053	+/-	197.027
Al	3201.777	+/-	567.634
P	503.062	+/-	102.290
Si	13686.150	+/-	568.176
Cl	1940.564	+/-	62.232
S	12795.513	+/-	262.081
Mg	1.000	+/-	4652.915

mRFA -Ergebnisse

XL3t-69288

Reading No 9
 Mode Mining
 Time 2018-08-02 11:19
 Duration 122.10
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P3 KRONE
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	88.071
La	1.000	+/-	73.170
Ba	1.000	+/-	76.944
Sb	1.000	+/-	27.455
Sn	54.768	+/-	22.566
Cd	16.625	+/-	11.439
Ag	201.588	+/-	17.387
Bal	874470.188	+/-	1114.806
Nb	1.000	+/-	15.158
Zr	1.000	+/-	34.791
Y	1.000	+/-	8.030
Sr	145.825	+/-	7.036
Rb	1.000	+/-	21.793
Th	1.000	+/-	490.640
Bi	1.000	+/-	408.900
Au	376.496	+/-	34.423
As	1373.067	+/-	83.520
Se	1.000	+/-	10.248
Pb	6209.841	+/-	117.861
Hg	1.000	+/-	9.611
Zn	272.283	+/-	25.976
Cu	4680.244	+/-	123.506
Ni	1.000	+/-	30.646
Co	1.000	+/-	46.576
Fe	2762.998	+/-	146.180
Mn	1.000	+/-	82.213
Cr	1.000	+/-	35.563
V	1.000	+/-	33.205
Ti	373.344	+/-	115.092
Ca	74959.352	+/-	1038.847
K	3271.917	+/-	210.262
Al	3862.250	+/-	707.917
P	1375.583	+/-	120.652
Si	16600.539	+/-	646.566
Cl	1341.010	+/-	52.159
S	7652.062	+/-	141.742
Mg	1.000	+/-	5834.086

mRFA -Ergebnisse

XL3t-69288

Reading No 10
 Mode Mining
 Time 2018-08-02 11:23
 Duration 121.82
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELENDE
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P4 NIMBUS EGIDIUS
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	90.649
La	1.000	+/-	74.401
Ba	1.000	+/-	78.777
Sb	1.000	+/-	27.271
Sn	23.868	+/-	21.362
Cd	13.294	+/-	11.385
Ag	195.107	+/-	16.954
Bal	892597.625	+/-	954.191
Nb	1.000	+/-	15.166
Zr	1.000	+/-	40.501
Y	1.000	+/-	9.433
Sr	126.327	+/-	6.647
Rb	1.000	+/-	23.660
Th	1.000	+/-	569.260
Bi	1.000	+/-	518.601
Au	280.476	+/-	33.764
As	2199.536	+/-	99.680
Se	1.000	+/-	11.113
Pb	8568.244	+/-	157.026
Hg	1.000	+/-	12.714
Zn	109.120	+/-	18.623
Cu	3351.241	+/-	100.681
Ni	1.000	+/-	30.746
Co	1.000	+/-	48.511
Fe	3180.952	+/-	154.705
Mn	1.000	+/-	80.702
Cr	33.369	+/-	25.118
V	1.000	+/-	29.123
Ti	468.231	+/-	118.950
Ca	58684.012	+/-	908.669
K	1887.926	+/-	182.912
Al	1119.106	+/-	568.963
P	2352.202	+/-	143.707
Si	9131.846	+/-	494.319
Cl	2594.759	+/-	72.418
S	13082.717	+/-	229.758
Mg	1.000	+/-	5524.176

mRFA -Ergebnisse

XL3t-69288

Reading No 11
 Mode Mining
 Time 2018-08-02 11:29
 Duration 121.95
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P5 KARL HELLBLAUE FARBSCHICHT
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	292.000
La	1.000	+/-	200.331
Ba	1.000	+/-	256.553
Sb	1.000	+/-	76.474
Sn	1526.947	+/-	107.085
Cd	1.000	+/-	33.714
Ag	1.000	+/-	26.001
Bal	841338.250	+/-	2428.015
Nb	69.936	+/-	65.031
Zr	1.000	+/-	196.337
Y	1.000	+/-	50.865
Sr	29.136	+/-	13.923
Rb	1.000	+/-	141.611
Th	1.000	+/-	3781.093
Bi	1.000	+/-	2067.236
Au	1.000	+/-	72.099
As	11808.073	+/-	475.128
Se	1.000	+/-	22.905
Pb	77325.156	+/-	2079.635
Hg	238.644	+/-	56.335
Zn	357.616	+/-	39.957
Cu	8831.796	+/-	289.050
Ni	1.000	+/-	52.931
Co	53.876	+/-	52.429
Fe	520.711	+/-	107.703
Mn	159.966	+/-	116.005
Cr	1.000	+/-	36.118
V	1.000	+/-	41.192
Ti	1.000	+/-	182.932
Ca	9649.199	+/-	365.617
K	1472.710	+/-	203.969
Al	2690.504	+/-	831.877
P	1960.590	+/-	187.197
Si	9493.182	+/-	614.234
Cl	3049.166	+/-	127.352
S	29424.551	+/-	953.423
Mg	1.000	+/-	8950.400

mRFA -Ergebnisse

XL3t-69288

Reading No 12
 Mode Mining
 Time 2018-08-02 11:35
 Duration 121.64
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P6 ZAUMZIERDE PFERD
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	104.699
La	1.000	+/-	87.490
Ba	1.000	+/-	92.811
Sb	1.000	+/-	42.778
Sn	49.011	+/-	26.990
Cd	21.518	+/-	13.846
Ag	254.901	+/-	22.531
Bal	893172.938	+/-	1084.725
Nb	13.869	+/-	12.985
Zr	1.000	+/-	46.858
Y	1.000	+/-	11.093
Sr	133.687	+/-	7.783
Rb	1.000	+/-	24.191
Th	1.000	+/-	656.069
Bi	1.000	+/-	590.429
Au	408.242	+/-	42.482
As	2220.616	+/-	115.140
Se	1.000	+/-	14.285
Pb	8784.257	+/-	182.985
Hg	1.000	+/-	13.478
Zn	169.624	+/-	21.955
Cu	395.511	+/-	38.457
Ni	1.000	+/-	33.915
Co	1.000	+/-	62.488
Fe	4657.869	+/-	216.648
Mn	1.000	+/-	94.076
Cr	1.000	+/-	38.346
V	1.000	+/-	30.132
Ti	633.109	+/-	156.982
Ca	63847.512	+/-	1116.596
K	1945.211	+/-	227.968
Al	695.661	+/-	631.818
P	3263.443	+/-	170.645
Si	7713.799	+/-	522.204
Cl	2407.759	+/-	79.556
S	9211.438	+/-	195.467
Mg	1.000	+/-	6225.881

mRFA -Ergebnisse

XL3t-69288

Reading No 13
 Mode Mining
 Time 2018-08-02 11:39
 Duration 122.11
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P7 ROTE FARBLASUR
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	244.744
La	1.000	+/-	149.013
Ba	1.000	+/-	156.577
Sb	1.000	+/-	58.644
Sn	1482.384	+/-	91.051
Cd	1.000	+/-	26.891
Ag	1.000	+/-	17.707
Bal	875348.875	+/-	1595.338
Nb	52.078	+/-	44.094
Zr	1.000	+/-	138.095
Y	1.000	+/-	35.120
Sr	42.402	+/-	11.194
Rb	1.000	+/-	98.560
Th	1.000	+/-	2598.198
Bi	1.000	+/-	1493.678
Au	1.000	+/-	59.602
As	9308.254	+/-	346.372
Se	1.000	+/-	26.977
Pb	54822.656	+/-	1315.858
Hg	785.975	+/-	52.107
Zn	285.630	+/-	29.811
Cu	290.224	+/-	35.494
Ni	1.000	+/-	46.496
Co	1.000	+/-	54.637
Fe	340.615	+/-	87.679
Mn	1.000	+/-	101.589
Cr	51.498	+/-	33.767
V	1.000	+/-	34.147
Ti	1.000	+/-	218.207
Ca	18238.059	+/-	542.095
K	2880.737	+/-	237.191
Al	3261.392	+/-	751.670
P	3790.782	+/-	206.375
Si	4682.356	+/-	429.093
Cl	2789.238	+/-	107.049
S	21546.748	+/-	624.863
Mg	1.000	+/-	7305.162

mRFA -Ergebnisse

XL3t-69288

Reading No 14
 Mode Mining
 Time 2018-08-02 11:43
 Duration 121.37
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELENDE
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P8 GRUENE RAHMUNG
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	181.095
La	1.000	+/-	145.949
Ba	1.000	+/-	153.514
Sb	1.000	+/-	51.632
Sn	2070.841	+/-	105.921
Cd	1.000	+/-	30.851
Ag	1.000	+/-	15.039
Bal	890798.938	+/-	1369.874
Nb	1.000	+/-	46.146
Zr	1.000	+/-	120.054
Y	1.000	+/-	30.092
Sr	147.607	+/-	11.472
Rb	1.000	+/-	87.316
Th	1.000	+/-	2234.299
Bi	1.000	+/-	1323.064
Au	1.000	+/-	41.036
As	7304.111	+/-	302.493
Se	1.000	+/-	19.736
Pb	40431.898	+/-	1022.960
Hg	1.000	+/-	23.552
Zn	1.000	+/-	45.696
Cu	18953.232	+/-	515.711
Ni	1.000	+/-	45.685
Co	1.000	+/-	44.810
Fe	735.604	+/-	99.943
Mn	1.000	+/-	94.593
Cr	1.000	+/-	51.868
V	1.000	+/-	24.359
Ti	1.000	+/-	116.695
Ca	7551.562	+/-	334.485
K	1380.190	+/-	230.714
Al	1.000	+/-	890.986
P	1028.359	+/-	148.155
Si	6261.567	+/-	478.060
Cl	2994.014	+/-	112.588
S	20342.143	+/-	576.559
Mg	1.000	+/-	7481.339

mRFA -Ergebnisse

XL3t-69288

Reading No 15
 Mode Mining
 Time 2018-08-02 11:47
 Duration 120.60
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P9 HIMMEL
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	135.702
La	1.000	+/-	111.149
Ba	1.000	+/-	179.068
Sb	1.000	+/-	70.697
Sn	35.392	+/-	27.774
Cd	1.000	+/-	18.546
Ag	1.000	+/-	13.525
Bal	858048.125	+/-	1500.845
Nb	1.000	+/-	26.539
Zr	1.000	+/-	77.822
Y	1.000	+/-	19.107
Sr	240.786	+/-	11.992
Rb	1.000	+/-	50.601
Th	1.000	+/-	1225.354
Bi	1.000	+/-	896.212
Au	1.000	+/-	28.618
As	3778.694	+/-	185.326
Se	1.000	+/-	17.113
Pb	20382.350	+/-	450.457
Hg	1.000	+/-	16.639
Zn	110.381	+/-	31.131
Cu	18685.771	+/-	451.711
Ni	1.000	+/-	39.852
Co	1.000	+/-	43.918
Fe	1203.305	+/-	115.753
Mn	1.000	+/-	125.144
Cr	1.000	+/-	31.434
V	1.000	+/-	30.096
Ti	143.115	+/-	133.929
Ca	52717.309	+/-	1054.627
K	1691.757	+/-	191.324
Al	2234.733	+/-	798.306
P	1366.798	+/-	171.097
Si	11241.101	+/-	621.679
Cl	2497.622	+/-	86.212
S	25622.777	+/-	537.913
Mg	1.000	+/-	7384.936

mRFA -Ergebnisse

XL3t-69288

Reading No 16
 Mode Mining
 Time 2018-08-02 11:55
 Duration 120.32
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P10 BLAU ERSTFASSUNG
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	64.097
La	1.000	+/-	52.681
Ba	1.000	+/-	56.333
Sb	1.000	+/-	28.768
Sn	151.640	+/-	19.262
Cd	19.811	+/-	8.977
Ag	6.246	+/-	5.580
Bal	918506.875	+/-	678.659
Nb	11.990	+/-	4.595
Zr	1.000	+/-	19.716
Y	7.761	+/-	3.913
Sr	35.589	+/-	3.111
Rb	1.000	+/-	8.948
Th	1.000	+/-	200.409
Bi	1.000	+/-	181.999
Au	1.000	+/-	6.465
As	1.000	+/-	37.629
Se	1.000	+/-	4.308
Pb	1026.271	+/-	29.988
Hg	11.064	+/-	4.251
Zn	1.000	+/-	15.729
Cu	2730.237	+/-	74.947
Ni	1.000	+/-	25.743
Co	1.000	+/-	41.621
Fe	692.552	+/-	74.512
Mn	1.000	+/-	65.677
Cr	1.000	+/-	26.096
V	1.000	+/-	38.628
Ti	174.064	+/-	151.242
Ca	35762.109	+/-	476.773
K	6286.243	+/-	242.427
Al	2010.808	+/-	538.971
P	639.349	+/-	99.172
Si	21280.965	+/-	694.494
Cl	4089.370	+/-	83.462
S	6557.139	+/-	113.815
Mg	1.000	+/-	4462.094

mRFA -Ergebnisse

XL3t-69288

Reading No 17
 Mode Mining
 Time 2018-08-02 12:00
 Duration 120.92
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P11 HELLGRUEN ZWEITFASSUNG
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	77.904
La	1.000	+/-	63.422
Ba	1.000	+/-	67.303
Sb	28.974	+/-	25.415
Sn	17.194	+/-	16.033
Cd	25.687	+/-	10.476
Ag	1.000	+/-	8.262
Bal	796633.813	+/-	1567.920
Nb	1.000	+/-	12.045
Zr	1.000	+/-	30.617
Y	1.000	+/-	7.087
Sr	80.125	+/-	5.046
Rb	1.000	+/-	18.022
Th	1.000	+/-	434.624
Bi	1.000	+/-	396.093
Au	1.000	+/-	13.116
As	559.364	+/-	64.345
Se	1.000	+/-	8.787
Pb	4463.734	+/-	85.875
Hg	1.000	+/-	7.732
Zn	1.000	+/-	20.828
Cu	18629.217	+/-	303.337
Ni	1.000	+/-	35.921
Co	536.305	+/-	72.098
Fe	4099.067	+/-	159.288
Mn	1.000	+/-	74.948
Cr	1.000	+/-	19.685
V	1.000	+/-	30.843
Ti	1.000	+/-	192.727
Ca	106374.375	+/-	1179.377
K	3695.662	+/-	195.300
Al	3875.511	+/-	740.854
P	1.000	+/-	91.974
Si	51752.695	+/-	1042.025
Cl	4214.533	+/-	81.144
S	5013.680	+/-	92.753
Mg	1.000	+/-	6056.932

mRFA -Ergebnisse

XL3t-69288

Reading No 18
 Mode Mining
 Time 2018-08-02 12:04
 Duration 121.21
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P12 TUERKIS
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	85.906
La	1.000	+/-	70.305
Ba	1.000	+/-	74.240
Sb	1.000	+/-	26.281
Sn	1.000	+/-	26.355
Cd	12.904	+/-	10.805
Ag	1.000	+/-	7.790
Bal	893449.938	+/-	961.940
Nb	14.594	+/-	13.274
Zr	1.000	+/-	47.541
Y	1.000	+/-	11.131
Sr	48.009	+/-	4.646
Rb	1.000	+/-	31.250
Th	1.000	+/-	761.764
Bi	1.000	+/-	552.908
Au	1.000	+/-	18.472
As	2647.097	+/-	116.048
Se	1.000	+/-	11.865
Pb	11371.002	+/-	218.437
Hg	1.000	+/-	10.666
Zn	160.105	+/-	17.770
Cu	972.843	+/-	50.924
Ni	1.000	+/-	30.678
Co	1.000	+/-	58.280
Fe	5254.111	+/-	206.018
Mn	1.000	+/-	75.094
Cr	1.000	+/-	27.575
V	1.000	+/-	21.955
Ti	1.000	+/-	80.390
Ca	21152.568	+/-	452.174
K	764.973	+/-	132.845
Al	4557.621	+/-	772.366
P	2915.790	+/-	194.254
Si	16668.020	+/-	696.355
Cl	4169.315	+/-	108.882
S	35841.215	+/-	672.143
Mg	1.000	+/-	9569.461

mRFA -Ergebnisse

XL3t-69288

Reading No 19
 Mode Mining
 Time 2018-08-02 12:09
 Duration 122.14
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags 3mm
 INV NR Gm12
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P13 HELLBLAU ZWEITFASSUNG
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	106.597
La	1.000	+/-	87.326
Ba	1491.371	+/-	124.419
Sb	1.000	+/-	42.909
Sn	28.165	+/-	22.075
Cd	1.000	+/-	12.111
Ag	1.000	+/-	12.077
Bal	742599.625	+/-	2237.240
Nb	1.000	+/-	16.500
Zr	1.000	+/-	60.499
Y	1.000	+/-	12.382
Sr	265.650	+/-	11.245
Rb	93.378	+/-	28.939
Th	1.000	+/-	910.357
Bi	1.000	+/-	1057.563
Au	1.000	+/-	37.946
As	9416.337	+/-	253.125
Se	1.000	+/-	23.664
Pb	8007.614	+/-	199.459
Hg	1.000	+/-	25.982
Zn	150.173	+/-	20.495
Cu	2201.976	+/-	93.541
Ni	1500.204	+/-	96.466
Co	4736.211	+/-	203.329
Fe	4975.875	+/-	227.611
Mn	349.924	+/-	171.176
Cr	1.000	+/-	53.121
V	1.000	+/-	251.908
Ti	778.539	+/-	754.276
Ca	12724.474	+/-	404.438
K	39291.414	+/-	1026.971
Al	5371.897	+/-	883.373
P	494.688	+/-	130.510
Si	157748.438	+/-	3292.552
Cl	2226.611	+/-	77.131
S	5547.361	+/-	150.869
Mg	1.000	+/-	5003.757