

mRFA -Ergebnisse

XL3t-69288

Reading No 1
Mode Mining
Time 2019-01-14 11:42
Duration 121.00
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1823
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P1 NIMBUS MARIA
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	64.993
La	1.000	+/-	29.721
Ba	1.000	+/-	32.031
Sb	1.000	+/-	12.340
Sn	10.907	+/-	6.252
Cd	10.323	+/-	4.627
Ag	8.046	+/-	3.151
Bal	770929.688	+/-	1041.094
Nb	1.000	+/-	4.639
Zr	1.000	+/-	20.458
Y	1.000	+/-	2.470
Sr	166.562	+/-	3.930
Rb	11.257	+/-	8.612
Th	1.000	+/-	281.283
Bi	476.523	+/-	217.915
Au	1391.741	+/-	30.675
As	45.521	+/-	14.971
Se	1.000	+/-	6.688
Pb	279.288	+/-	10.979
Hg	6.416	+/-	3.566
Zn	54.592	+/-	9.290
Cu	13.015	+/-	10.306
Ni	1.000	+/-	19.859
Co	1.000	+/-	40.881
Fe	9978.200	+/-	158.879
Mn	1.000	+/-	48.583
Cr	88.828	+/-	18.716
V	25.696	+/-	20.527
Ti	1146.274	+/-	124.523
Ca	116465.805	+/-	864.585
K	2733.932	+/-	149.177
Al	18219.730	+/-	1196.784
P	26507.027	+/-	337.684
Si	42945.164	+/-	862.435
Cl	557.980	+/-	27.330
S	7927.365	+/-	106.731
Mg	1.000	+/-	6524.526

mRFA -Ergebnisse

XL3t-69288

Reading No 2
Mode Mining
Time 2019-01-14 11:46
Duration 121.61
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1823
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P2 NIMBUS CHRISTUS
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	75.151
La	1.000	+/-	34.517
Ba	1.000	+/-	37.164
Sb	1.000	+/-	14.171
Sn	12.530	+/-	7.201
Cd	11.913	+/-	5.324
Ag	14.734	+/-	3.866
Bal	708608.250	+/-	1333.237
Nb	1.000	+/-	9.261
Zr	1.000	+/-	38.026
Y	1.000	+/-	3.333
Sr	263.407	+/-	5.370
Rb	13.315	+/-	11.207
Th	1.000	+/-	363.505
Bi	874.644	+/-	280.828
Au	2253.849	+/-	42.982
As	56.255	+/-	19.085
Se	1.000	+/-	8.645
Pb	417.341	+/-	14.256
Hg	13.485	+/-	4.679
Zn	93.878	+/-	11.817
Cu	47.791	+/-	12.399
Ni	1.000	+/-	22.550
Co	1.000	+/-	55.021
Fe	17712.867	+/-	245.581
Mn	83.856	+/-	55.502
Cr	129.683	+/-	27.249
V	46.869	+/-	32.640
Ti	1920.831	+/-	194.208
Ca	132430.203	+/-	1046.405
K	4159.090	+/-	199.115
Al	26118.283	+/-	1639.278
P	36085.273	+/-	440.597
Si	54813.973	+/-	1044.578
Cl	646.132	+/-	32.981
S	13171.536	+/-	160.375
Mg	1.000	+/-	8183.810

mRFA -Ergebnisse

XL3t-69288

Reading No 3
Mode Mining
Time 2019-01-14 11:49
Duration 120.71
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1823
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P3 MUETZE HIRTE
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	113.949
La	1.000	+/-	52.248
Ba	1.000	+/-	55.873
Sb	1.000	+/-	25.045
Sn	29.189	+/-	10.615
Cd	9.387	+/-	7.372
Ag	5.088	+/-	4.843
Bal	872954.250	+/-	971.913
Nb	28.742	+/-	16.876
Zr	1.000	+/-	57.979
Y	1.000	+/-	14.570
Sr	139.811	+/-	9.148
Rb	1.000	+/-	27.763
Th	1.000	+/-	818.116
Bi	1.000	+/-	782.024
Au	1.000	+/-	46.157
As	7126.802	+/-	171.727
Se	23.608	+/-	16.863
Pb	23206.254	+/-	353.939
Hg	3922.355	+/-	70.025
Zn	329.119	+/-	26.759
Cu	1403.980	+/-	49.289
Ni	1.000	+/-	34.050
Co	1.000	+/-	40.154
Fe	1266.429	+/-	83.653
Mn	73.378	+/-	70.677
Cr	1.000	+/-	26.688
V	1.000	+/-	25.781
Ti	1.000	+/-	88.119
Ca	16910.652	+/-	316.757
K	2705.298	+/-	162.502
Al	6779.512	+/-	810.504
P	5212.788	+/-	195.259
Si	15897.356	+/-	556.857
Cl	2502.513	+/-	58.432
S	39473.492	+/-	629.142
Mg	1.000	+/-	10451.664

mRFA -Ergebnisse

XL3t-69288

Reading No 5
Mode Mining
Time 2019-01-14 11:55
Duration 120.32
Units ppm
Sigma Value 2
Sequence Final
Flags 3mm
INV NR Gm1823
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P4 INKARNAT JOSEF
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	165.424
La	1.000	+/-	134.372
Ba	1.000	+/-	140.991
Sb	1.000	+/-	46.710
Sn	185.594	+/-	40.810
Cd	1.000	+/-	21.002
Ag	1.000	+/-	14.224
Bal	860871.563	+/-	1626.094
Nb	56.418	+/-	33.085
Zr	1.000	+/-	108.154
Y	1.000	+/-	28.131
Sr	149.745	+/-	12.853
Rb	1.000	+/-	56.929
Th	1.000	+/-	1443.543
Bi	1.000	+/-	1314.145
Au	1.000	+/-	55.879
As	8937.267	+/-	292.981
Se	34.232	+/-	24.452
Pb	38201.648	+/-	821.058
Hg	1078.399	+/-	54.497
Zn	209.599	+/-	28.534
Cu	1477.336	+/-	75.053
Ni	1.000	+/-	46.054
Co	1.000	+/-	63.327
Fe	379.692	+/-	90.884
Mn	124.605	+/-	107.542
Cr	1.000	+/-	35.494
V	1.000	+/-	29.005
Ti	1.000	+/-	117.075
Ca	9914.796	+/-	319.266
K	1393.879	+/-	188.942
Al	5192.709	+/-	987.896
P	5103.760	+/-	270.579
Si	17123.498	+/-	818.917
Cl	3992.545	+/-	128.447
S	45572.805	+/-	1044.460
Mg	1.000	+/-	10636.213

mRFA -Ergebnisse

XL3t-69288

Reading No 6
Mode Mining
Time 2019-01-14 11:58
Duration 120.88
Units ppm
Sigma Value 2
Sequence Final
Flags 3mm
INV NR Gm1823
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P5 KRAGEN HIRTE
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	155.212
La	1.000	+/-	128.651
Ba	1.000	+/-	137.112
Sb	1.000	+/-	46.591
Sn	1.000	+/-	32.135
Cd	1.000	+/-	22.440
Ag	1.000	+/-	10.469
Bal	838437.500	+/-	1864.592
Nb	1.000	+/-	19.404
Zr	1.000	+/-	66.088
Y	1.000	+/-	16.118
Sr	130.844	+/-	9.759
Rb	1.000	+/-	29.154
Th	1.000	+/-	903.421
Bi	1.000	+/-	860.897
Au	1.000	+/-	27.416
As	1971.279	+/-	151.126
Se	1.000	+/-	22.714
Pb	11022.196	+/-	260.286
Hg	1.000	+/-	17.050
Zn	1.000	+/-	57.455
Cu	91169.453	+/-	1482.210
Ni	1.000	+/-	43.009
Co	1.000	+/-	47.059
Fe	892.687	+/-	94.559
Mn	1.000	+/-	134.362
Cr	1.000	+/-	29.798
V	1.000	+/-	25.925
Ti	165.684	+/-	125.414
Ca	28126.309	+/-	522.880
K	1674.048	+/-	184.471
Al	1490.560	+/-	794.099
P	603.899	+/-	130.954
Si	9506.032	+/-	574.462
Cl	1942.680	+/-	71.538
S	12866.769	+/-	245.901
Mg	1.000	+/-	9146.122

mRFA -Ergebnisse

XL3t-69288

Reading No 7
Mode Mining
Time 2019-01-14 12:02
Duration 122.26
Units ppm
Sigma Value 2
Sequence Final
Flags 3mm
INV NR Gm1823
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P6 UNTERGEWAND JOSEF
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	125.637
La	1.000	+/-	103.102
Ba	1.000	+/-	108.916
Sb	1.000	+/-	37.763
Sn	1.000	+/-	32.749
Cd	1.000	+/-	13.680
Ag	1.000	+/-	8.313
Bal	897480.750	+/-	1095.891
Nb	16.026	+/-	15.654
Zr	1.000	+/-	55.978
Y	1.000	+/-	13.661
Sr	184.175	+/-	9.589
Rb	1.000	+/-	27.065
Th	1.000	+/-	776.987
Bi	1.000	+/-	756.144
Au	1.000	+/-	23.580
As	3225.117	+/-	146.149
Se	16.885	+/-	14.411
Pb	13022.904	+/-	272.011
Hg	1.000	+/-	15.984
Zn	39.974	+/-	18.120
Cu	4996.805	+/-	154.973
Ni	1.000	+/-	36.686
Co	1.000	+/-	45.771
Fe	1206.723	+/-	117.692
Mn	1.000	+/-	95.624
Cr	1.000	+/-	31.410
V	1.000	+/-	21.489
Ti	1.000	+/-	115.165
Ca	31237.688	+/-	676.244
K	1707.716	+/-	187.534
Al	8761.079	+/-	970.986
P	1408.669	+/-	155.506
Si	13686.966	+/-	666.203
Cl	3205.375	+/-	97.483
S	19803.104	+/-	419.244
Mg	1.000	+/-	7093.798

mRFA -Ergebnisse

XL3t-69288

Reading No 8
Mode Mining
Time 2019-01-14 12:06
Duration 120.73
Units ppm
Sigma Value 2
Sequence Final
Flags 3mm
INV NR Gm1823
OBJEKT TAFELGEMAELENDE
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P7 KLEID MARIA
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	159.045
La	1.000	+/-	130.988
Ba	1.000	+/-	138.088
Sb	1.000	+/-	46.720
Sn	1.000	+/-	31.858
Cd	42.766	+/-	20.761
Ag	1.000	+/-	10.187
Bal	842450.813	+/-	1847.347
Nb	1.000	+/-	22.223
Zr	1.000	+/-	74.744
Y	1.000	+/-	18.988
Sr	112.576	+/-	9.587
Rb	1.000	+/-	36.855
Th	1.000	+/-	1032.224
Bi	1.000	+/-	936.523
Au	1.000	+/-	28.832
As	1594.170	+/-	168.199
Se	1.000	+/-	25.136
Pb	14663.438	+/-	339.491
Hg	1.000	+/-	16.928
Zn	1.000	+/-	59.587
Cu	106429.469	+/-	1678.399
Ni	1.000	+/-	43.426
Co	225.755	+/-	56.838
Fe	1298.860	+/-	103.986
Mn	101.844	+/-	83.078
Cr	1.000	+/-	30.663
V	1.000	+/-	24.271
Ti	169.468	+/-	118.011
Ca	7679.619	+/-	223.270
K	1178.923	+/-	164.317
Al	1709.728	+/-	687.405
P	453.654	+/-	107.750
Si	9054.480	+/-	502.911
Cl	1087.145	+/-	51.159
S	11747.247	+/-	225.030
Mg	1.000	+/-	7466.518