

mRFA -Ergebnisse

XL3t-69288

Reading No 14
Mode Mining
Time 2020-04-09 11:26
Duration 120.35
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1637
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P1 KLEID MARIA
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	62.628
La	1.000	+/-	28.752
Ba	100.090	+/-	33.438
Sb	1.000	+/-	15.548
Sn	1.000	+/-	7.009
Cd	20.660	+/-	4.828
Ag	516.925	+/-	11.924
Bal	858601.938	+/-	694.553
Nb	5.307	+/-	3.728
Zr	1.000	+/-	13.094
Y	1.000	+/-	2.893
Sr	201.072	+/-	4.360
Rb	1.000	+/-	6.063
Th	1.000	+/-	190.078
Bi	1.000	+/-	171.247
Au	1.000	+/-	5.294
As	1.000	+/-	29.047
Se	1.000	+/-	3.890
Pb	2391.119	+/-	32.009
Hg	22.667	+/-	3.401
Zn	332.459	+/-	14.239
Cu	148.762	+/-	14.271
Ni	1.000	+/-	19.280
Co	1.000	+/-	18.807
Fe	981.039	+/-	53.228
Mn	1.000	+/-	44.898
Cr	1.000	+/-	16.794
V	1.000	+/-	13.043
Ti	1.000	+/-	104.611
Ca	102223.141	+/-	717.382
K	6042.872	+/-	181.920
Al	5051.040	+/-	839.315
P	2146.691	+/-	141.038
Si	6943.827	+/-	431.264
Cl	3327.270	+/-	57.842
S	10943.024	+/-	134.901
Mg	1.000	+/-	6489.176

mRFA -Ergebnisse

XL3t-69288

Reading No 15
Mode Mining
Time 2020-04-09 11:30
Duration 120.57
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1637
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P2 KLEID MARIA
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	63.286
La	1.000	+/-	28.931
Ba	91.306	+/-	33.530
Sb	1.000	+/-	10.741
Sn	1.000	+/-	7.022
Cd	24.530	+/-	4.915
Ag	550.309	+/-	11.992
Bal	837330.500	+/-	775.735
Nb	1.000	+/-	3.566
Zr	1.000	+/-	10.408
Y	1.000	+/-	3.750
Sr	193.117	+/-	4.166
Rb	1.000	+/-	4.963
Th	1.000	+/-	156.665
Bi	1.000	+/-	132.356
Au	1.000	+/-	4.668
As	1.000	+/-	23.522
Se	5.742	+/-	3.909
Pb	1628.391	+/-	24.657
Hg	13.451	+/-	2.734
Zn	120.428	+/-	9.347
Cu	42.840	+/-	11.212
Ni	1.000	+/-	19.545
Co	1.000	+/-	16.317
Fe	530.104	+/-	43.263
Mn	1.000	+/-	45.016
Cr	1.000	+/-	17.239
V	1.000	+/-	19.392
Ti	1.000	+/-	115.037
Ca	124196.461	+/-	770.550
K	2970.318	+/-	158.045
Al	3561.410	+/-	707.013
P	3513.052	+/-	133.920
Si	6383.377	+/-	369.269
Cl	2508.570	+/-	44.096
S	8276.690	+/-	100.128
Mg	8059.449	+/-	6991.630

mRFA -Ergebnisse

XL3t-69288

Reading No 16
Mode Mining
Time 2020-04-09 11:33
Duration 122.23
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1637
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P3 KLEID MARIA RETUSCHE
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	64.191
La	1.000	+/-	29.497
Ba	207.012	+/-	35.126
Sb	1.000	+/-	14.122
Sn	1.000	+/-	7.256
Cd	22.462	+/-	4.975
Ag	530.948	+/-	12.281
Bal	790440.000	+/-	946.879
Nb	1.000	+/-	5.042
Zr	1.000	+/-	14.770
Y	9.518	+/-	3.558
Sr	217.411	+/-	4.507
Rb	1.000	+/-	5.916
Th	1.000	+/-	190.900
Bi	1.000	+/-	186.369
Au	1.000	+/-	7.605
As	1.000	+/-	27.021
Se	4.693	+/-	4.504
Pb	2338.724	+/-	31.276
Hg	32.292	+/-	2.855
Zn	70.619	+/-	8.021
Cu	21.733	+/-	10.699
Ni	1.000	+/-	19.579
Co	1.000	+/-	17.811
Fe	781.035	+/-	48.744
Mn	1.000	+/-	46.113
Cr	58.894	+/-	16.169
V	1.000	+/-	21.606
Ti	1.000	+/-	147.152
Ca	167775.188	+/-	1018.093
K	8376.661	+/-	251.601
Al	6384.176	+/-	1007.489
P	1781.216	+/-	133.143
Si	11111.542	+/-	507.372
Cl	2316.108	+/-	49.417
S	7519.868	+/-	104.489
Mg	1.000	+/-	9375.891

mRFA -Ergebnisse

XL3t-69288

Reading No 17
Mode Mining
Time 2020-04-09 11:37
Duration 120.59
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1637
OBJEKT TAFELGEMAELE
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P4 FLUEGEL ENGEL
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	64.510
La	1.000	+/-	29.648
Ba	242.103	+/-	35.135
Sb	1.000	+/-	13.483
Sn	1.000	+/-	9.412
Cd	11.129	+/-	4.580
Ag	9.146	+/-	3.154
Bal	788091.813	+/-	938.892
Nb	1.000	+/-	3.064
Zr	1.000	+/-	9.916
Y	9.145	+/-	2.854
Sr	177.557	+/-	4.058
Rb	17.318	+/-	5.444
Th	1.000	+/-	149.263
Bi	1.000	+/-	116.242
Au	2735.844	+/-	43.031
As	1.000	+/-	18.226
Se	1.000	+/-	5.583
Pb	1192.897	+/-	20.734
Hg	29.170	+/-	4.336
Zn	181.054	+/-	13.440
Cu	11.819	+/-	10.122
Ni	1.000	+/-	19.274
Co	1.000	+/-	15.984
Fe	416.561	+/-	40.252
Mn	1.000	+/-	45.251
Cr	45.725	+/-	15.719
V	1.000	+/-	14.073
Ti	1.000	+/-	119.468
Ca	162047.906	+/-	906.752
K	555.900	+/-	110.458
Al	1260.024	+/-	846.867
P	29788.188	+/-	362.457
Si	2418.646	+/-	468.589
Cl	1699.171	+/-	43.331
S	9058.902	+/-	117.492
Mg	1.000	+/-	8539.501

mRFA -Ergebnisse

XL3t-69288

Reading No 18
Mode Mining
Time 2020-04-09 11:40
Duration 121.68
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1637
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P5 FLUEGEL ENGEL
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	68.167
La	1.000	+/-	31.361
Ba	1.000	+/-	55.685
Sb	1.000	+/-	11.551
Sn	1.000	+/-	5.684
Cd	14.539	+/-	4.973
Ag	13.786	+/-	3.541
Bal	761764.938	+/-	1091.401
Nb	1.000	+/-	2.593
Zr	1.000	+/-	10.261
Y	8.237	+/-	2.881
Sr	249.296	+/-	5.141
Rb	32.196	+/-	6.475
Th	1.000	+/-	190.025
Bi	1.000	+/-	119.428
Au	5288.107	+/-	67.045
As	1.000	+/-	16.503
Se	1.000	+/-	7.564
Pb	884.109	+/-	18.704
Hg	23.962	+/-	5.818
Zn	98.214	+/-	14.782
Cu	19.606	+/-	11.316
Ni	1.000	+/-	21.042
Co	1.000	+/-	17.973
Fe	430.958	+/-	42.623
Mn	1.000	+/-	46.928
Cr	84.111	+/-	18.710
V	1.000	+/-	13.225
Ti	1.000	+/-	98.088
Ca	161173.094	+/-	969.873
K	597.499	+/-	118.835
Al	1214.510	+/-	1004.911
P	52611.961	+/-	513.804
Si	1.000	+/-	537.995
Cl	1385.722	+/-	46.448
S	14105.226	+/-	160.018
Mg	1.000	+/-	11284.902

mRFA -Ergebnisse

XL3t-69288

Reading No 19
Mode Mining
Time 2020-04-09 11:44
Duration 121.24
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1637
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P6 JESUSKIND RETUSCHE
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	108.402
La	1.000	+/-	49.537
Ba	275.307	+/-	57.220
Sb	29.333	+/-	18.993
Sn	44.547	+/-	10.594
Cd	17.602	+/-	7.358
Ag	5.431	+/-	4.678
Bal	888148.125	+/-	839.273
Nb	23.622	+/-	14.508
Zr	1.000	+/-	51.435
Y	1.000	+/-	12.584
Sr	186.104	+/-	7.057
Rb	1.000	+/-	23.478
Th	1.000	+/-	734.820
Bi	1.000	+/-	737.016
Au	1.000	+/-	17.489
As	4153.158	+/-	136.994
Se	1.000	+/-	20.078
Pb	18134.279	+/-	276.649
Hg	1.000	+/-	9.849
Zn	35321.559	+/-	494.681
Cu	21.730	+/-	17.281
Ni	1.000	+/-	27.592
Co	1.000	+/-	23.945
Fe	648.349	+/-	58.790
Mn	88.159	+/-	62.235
Cr	53.214	+/-	20.909
V	1.000	+/-	20.071
Ti	373.032	+/-	110.987
Ca	13782.723	+/-	244.314
K	118.046	+/-	95.114
Al	1165.596	+/-	498.555
P	1567.933	+/-	115.036
Si	6998.373	+/-	322.515
Cl	2360.750	+/-	47.634
S	26482.980	+/-	379.156
Mg	1.000	+/-	5833.888

mRFA -Ergebnisse

XL3t-69288

Reading No 20
Mode Mining
Time 2020-04-09 11:48
Duration 122.85
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1637
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P7 MANTEL MARIA
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	161.228
La	1.000	+/-	73.507
Ba	1081.510	+/-	92.022
Sb	1.000	+/-	31.209
Sn	231.912	+/-	19.715
Cd	1.000	+/-	15.485
Ag	17.445	+/-	7.131
Bal	785709.563	+/-	2074.440
Nb	65.074	+/-	33.984
Zr	1.000	+/-	112.717
Y	1.000	+/-	29.329
Sr	103.481	+/-	9.061
Rb	1.000	+/-	55.570
Th	1.000	+/-	1558.500
Bi	1.000	+/-	1429.392
Au	950.826	+/-	65.680
As	7286.480	+/-	275.640
Se	1.000	+/-	24.870
Pb	50010.840	+/-	899.273
Hg	1.000	+/-	21.739
Zn	1.000	+/-	39.698
Cu	71523.930	+/-	1080.455
Ni	1.000	+/-	40.018
Co	1.000	+/-	40.513
Fe	1839.345	+/-	98.489
Mn	210.525	+/-	79.821
Cr	1.000	+/-	25.687
V	1.000	+/-	39.238
Ti	1.000	+/-	191.895
Ca	13202.969	+/-	284.563
K	3084.606	+/-	196.969
Al	3340.361	+/-	780.589
P	12351.866	+/-	277.756
Si	15541.951	+/-	543.117
Cl	5439.621	+/-	103.794
S	28007.725	+/-	463.169
Mg	1.000	+/-	8281.248