

mRFA -Ergebnisse

XL3t-69288

Reading No 1
Mode Mining
Time 2019-10-11 11:58
Duration 122.20
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm309
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P1 RAHMEN
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	61.866
La	1.000	+/-	28.310
Ba	1.000	+/-	30.564
Sb	1.000	+/-	17.763
Sn	13.146	+/-	5.897
Cd	17.348	+/-	4.507
Ag	4.913	+/-	2.841
Bal	903970.313	+/-	541.290
Nb	22.071	+/-	7.686
Zr	1.000	+/-	31.106
Y	1.000	+/-	6.274
Sr	33.434	+/-	2.543
Rb	1.000	+/-	14.301
Th	1.000	+/-	401.262
Bi	1.000	+/-	387.427
Au	1.000	+/-	12.048
As	2374.122	+/-	73.719
Se	1.000	+/-	9.471
Pb	9939.390	+/-	116.316
Hg	1.000	+/-	5.805
Zn	207.269	+/-	13.019
Cu	1993.448	+/-	46.022
Ni	1.000	+/-	21.383
Co	1.000	+/-	53.666
Fe	15198.616	+/-	235.613
Mn	1.000	+/-	51.677
Cr	1.000	+/-	27.956
V	34.481	+/-	31.505
Ti	190.787	+/-	162.971
Ca	30252.986	+/-	365.389
K	3026.308	+/-	144.047
Al	1652.191	+/-	396.387
P	757.623	+/-	73.930
Si	14107.792	+/-	394.006
Cl	1475.420	+/-	30.170
S	8897.574	+/-	115.710
Mg	5830.815	+/-	4206.205

mRFA -Ergebnisse

XL3t-69288

Reading No 2
Mode Mining
Time 2019-10-11 12:02
Duration 122.08
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm309
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P2 RAHMEN
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	98.653
La	1.000	+/-	45.083
Ba	1.000	+/-	48.381
Sb	60.520	+/-	17.954
Sn	1.000	+/-	11.096
Cd	6.765	+/-	6.427
Ag	1.000	+/-	3.444
Bal	907941.688	+/-	631.491
Nb	34.738	+/-	13.655
Zr	1.000	+/-	47.324
Y	1.000	+/-	11.472
Sr	29.427	+/-	3.416
Rb	1.000	+/-	23.055
Th	1.000	+/-	675.936
Bi	1.000	+/-	692.030
Au	1.000	+/-	17.657
As	4985.678	+/-	133.067
Se	12.230	+/-	10.726
Pb	20534.268	+/-	287.182
Hg	1.000	+/-	9.353
Zn	75.953	+/-	9.281
Cu	153.286	+/-	18.463
Ni	1.000	+/-	28.055
Co	1.000	+/-	30.260
Fe	1756.075	+/-	85.601
Mn	1.000	+/-	58.819
Cr	28.472	+/-	16.464
V	1.000	+/-	17.344
Ti	1.000	+/-	118.225
Ca	32175.383	+/-	483.429
K	2175.755	+/-	128.890
Al	1464.507	+/-	503.793
P	2066.920	+/-	118.701
Si	7748.048	+/-	362.610
Cl	1656.333	+/-	41.377
S	17093.934	+/-	270.666
Mg	1.000	+/-	5350.182

mRFA -Ergebnisse

XL3t-69288

Reading No 3
Mode Mining
Time 2019-10-11 12:08
Duration 120.45
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm309
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P3 RAHMEN
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	99.418
La	1.000	+/-	45.478
Ba	1.000	+/-	49.681
Sb	1.000	+/-	23.701
Sn	1.000	+/-	8.802
Cd	7.305	+/-	6.502
Ag	1.000	+/-	5.453
Bal	881160.500	+/-	804.385
Nb	34.305	+/-	13.748
Zr	1.000	+/-	47.927
Y	1.000	+/-	11.593
Sr	50.603	+/-	3.953
Rb	1.000	+/-	22.259
Th	1.000	+/-	688.171
Bi	1.000	+/-	689.313
Au	1.000	+/-	16.874
As	4506.471	+/-	130.630
Se	1.000	+/-	17.265
Pb	20246.689	+/-	283.894
Hg	1.000	+/-	9.486
Zn	123.984	+/-	11.628
Cu	358.566	+/-	24.399
Ni	1.000	+/-	29.833
Co	1.000	+/-	64.189
Fe	14148.607	+/-	282.808
Mn	1.000	+/-	68.293
Cr	36.815	+/-	22.647
V	1.000	+/-	59.273
Ti	1.000	+/-	323.961
Ca	50201.188	+/-	682.649
K	2451.270	+/-	155.041
Al	1229.644	+/-	523.670
P	836.169	+/-	99.389
Si	10080.789	+/-	404.259
Cl	1544.751	+/-	38.686
S	12982.341	+/-	199.557
Mg	1.000	+/-	5118.430

mRFA -Ergebnisse

XL3t-69288

Reading No 4
Mode Mining
Time 2019-10-11 12:13
Duration 120.81
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm309
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P4 NIMBUS
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	72.551
La	1.000	+/-	33.471
Ba	1.000	+/-	36.182
Sb	1.000	+/-	19.534
Sn	47.375	+/-	8.189
Cd	17.443	+/-	5.609
Ag	7.797	+/-	3.662
Bal	798709.313	+/-	1030.723
Nb	16.550	+/-	3.748
Zr	18.714	+/-	12.719
Y	1.000	+/-	2.720
Sr	39.593	+/-	2.304
Rb	7.131	+/-	5.514
Th	1.000	+/-	181.312
Bi	1.000	+/-	191.503
Au	1.000	+/-	5.800
As	547.947	+/-	31.792
Se	1.000	+/-	3.871
Pb	1821.144	+/-	29.461
Hg	1.000	+/-	3.036
Zn	26.176	+/-	7.296
Cu	363.655	+/-	21.069
Ni	1.000	+/-	22.589
Co	1.000	+/-	52.290
Fe	13027.048	+/-	193.031
Mn	1.000	+/-	50.351
Cr	68.939	+/-	27.270
V	50.768	+/-	30.948
Ti	941.058	+/-	171.896
Ca	128985.586	+/-	890.752
K	6039.824	+/-	221.341
Al	2732.853	+/-	980.052
P	1.000	+/-	200.478
Si	25032.625	+/-	765.031
Cl	1745.691	+/-	48.876
S	7707.419	+/-	116.226
Mg	12045.309	+/-	10170.115

mRFA -Ergebnisse

XL3t-69288

Reading No 5
Mode Mining
Time 2019-10-11 12:17
Duration 121.12
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm309
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P5 UNTERZEICHNUNG
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	82.253
La	1.000	+/-	37.770
Ba	1.000	+/-	40.688
Sb	1.000	+/-	18.061
Sn	13.605	+/-	7.773
Cd	16.759	+/-	5.914
Ag	1.000	+/-	5.109
Bal	878188.688	+/-	775.735
Nb	41.371	+/-	12.479
Zr	1.000	+/-	50.305
Y	1.000	+/-	10.563
Sr	37.188	+/-	3.354
Rb	1.000	+/-	20.160
Th	1.000	+/-	625.050
Bi	1.000	+/-	673.186
Au	1.000	+/-	15.692
As	5311.618	+/-	127.964
Se	15.493	+/-	11.066
Pb	19126.170	+/-	257.067
Hg	1.000	+/-	9.173
Zn	129.248	+/-	10.989
Cu	478.996	+/-	25.588
Ni	1.000	+/-	25.556
Co	1.000	+/-	27.393
Fe	1368.128	+/-	73.702
Mn	1.000	+/-	52.666
Cr	1.000	+/-	32.756
V	1.000	+/-	25.145
Ti	1.000	+/-	98.024
Ca	53779.680	+/-	719.832
K	2560.589	+/-	149.024
Al	2580.654	+/-	657.806
P	1450.967	+/-	134.971
Si	9286.125	+/-	431.105
Cl	2406.059	+/-	53.154
S	23208.633	+/-	334.748
Mg	1.000	+/-	7539.187

mRFA -Ergebnisse

XL3t-69288

Reading No 6
Mode Mining
Time 2019-10-11 12:21
Duration 121.65
Units ppm
Sigma Value 2
Sequence Final
Flags 3mm
INV NR Gm309
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P6 UNTERZEICHNUNG SPOT
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	104.493
La	1.000	+/-	85.985
Ba	1.000	+/-	90.890
Sb	1.000	+/-	44.172
Sn	1.000	+/-	35.415
Cd	1.000	+/-	20.173
Ag	1.000	+/-	8.891
Bal	870219.625	+/-	1340.270
Nb	31.928	+/-	17.085
Zr	1.000	+/-	64.161
Y	1.000	+/-	14.912
Sr	40.082	+/-	5.354
Rb	1.000	+/-	33.775
Th	1.000	+/-	839.827
Bi	1.000	+/-	808.197
Au	1.000	+/-	25.021
As	4029.714	+/-	163.406
Se	1.000	+/-	22.582
Pb	15262.272	+/-	315.613
Hg	1.000	+/-	15.180
Zn	164.535	+/-	20.196
Cu	560.382	+/-	45.265
Ni	1.000	+/-	36.487
Co	1.000	+/-	48.548
Fe	1684.233	+/-	135.805
Mn	1.000	+/-	84.046
Cr	1.000	+/-	34.947
V	1.000	+/-	38.532
Ti	1.000	+/-	160.584
Ca	63867.461	+/-	1214.934
K	2821.392	+/-	232.820
Al	2769.524	+/-	848.020
P	1285.641	+/-	174.095
Si	10098.203	+/-	611.036
Cl	3678.733	+/-	108.563
S	23486.184	+/-	470.199
Mg	1.000	+/-	15079.530

mRFA -Ergebnisse

XL3t-69288

Reading No 7
Mode Mining
Time 2019-10-11 12:25
Duration 121.02
Units ppm
Sigma Value 2
Sequence Final
Flags 3mm
INV NR Gm309
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P7 keine UNTERZEICHNUNG SPOT
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	131.668
La	1.000	+/-	107.928
Ba	1.000	+/-	112.378
Sb	1.000	+/-	38.971
Sn	1.000	+/-	36.533
Cd	1.000	+/-	17.798
Ag	1.000	+/-	13.116
Bal	869374.438	+/-	1476.685
Nb	56.328	+/-	28.593
Zr	1.000	+/-	95.127
Y	1.000	+/-	24.364
Sr	36.252	+/-	6.725
Rb	1.000	+/-	52.642
Th	1.000	+/-	1290.914
Bi	1.000	+/-	1142.943
Au	1.000	+/-	36.195
As	7404.363	+/-	256.366
Se	22.416	+/-	17.775
Pb	32115.865	+/-	676.326
Hg	1.000	+/-	21.551
Zn	98.216	+/-	15.482
Cu	326.735	+/-	36.914
Ni	1.000	+/-	40.801
Co	1.000	+/-	52.550
Fe	1010.650	+/-	114.962
Mn	1.000	+/-	136.832
Cr	1.000	+/-	35.990
V	1.000	+/-	26.567
Ti	1.000	+/-	131.170
Ca	40563.375	+/-	898.425
K	2164.999	+/-	217.055
Al	2489.016	+/-	836.570
P	1584.005	+/-	186.806
Si	10036.112	+/-	618.354
Cl	4272.087	+/-	129.025
S	28445.104	+/-	628.547
Mg	1.000	+/-	7975.786

mRFA -Ergebnisse

XL3t-69288

Reading No 8
Mode Mining
Time 2019-10-11 12:29
Duration 120.55
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm309
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P8 MANTEL ROTLACK
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	95.908
La	1.000	+/-	43.665
Ba	1.000	+/-	46.732
Sb	1.000	+/-	24.687
Sn	9.665	+/-	8.778
Cd	13.935	+/-	6.641
Ag	6.117	+/-	4.317
Bal	882453.250	+/-	802.994
Nb	46.856	+/-	14.211
Zr	1.000	+/-	56.838
Y	1.000	+/-	11.993
Sr	40.339	+/-	3.714
Rb	1.000	+/-	25.752
Th	1.000	+/-	703.435
Bi	1.000	+/-	769.826
Au	1.000	+/-	17.430
As	5816.521	+/-	144.556
Se	12.078	+/-	10.993
Pb	20880.490	+/-	297.463
Hg	1.000	+/-	9.925
Zn	81.072	+/-	9.935
Cu	730.879	+/-	33.049
Ni	1.000	+/-	28.787
Co	1.000	+/-	30.301
Fe	1770.845	+/-	87.357
Mn	1.000	+/-	57.027
Cr	1.000	+/-	30.179
V	1.000	+/-	22.625
Ti	110.186	+/-	109.499
Ca	46420.617	+/-	686.379
K	4942.766	+/-	203.174
Al	2212.221	+/-	723.440
P	1078.620	+/-	137.768
Si	10929.567	+/-	503.939
Cl	2593.280	+/-	62.020
S	19850.688	+/-	320.930
Mg	1.000	+/-	6727.193

mRFA -Ergebnisse

XL3t-69288

Reading No 9
Mode Mining
Time 2019-10-11 12:33
Duration 121.91
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm309
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P9 NISCHE
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	65.551
La	1.000	+/-	30.268
Ba	1.000	+/-	32.674
Sb	18.273	+/-	12.253
Sn	13.510	+/-	6.445
Cd	17.229	+/-	4.960
Ag	4.226	+/-	3.093
Bal	833665.063	+/-	777.245
Nb	9.206	+/-	3.235
Zr	1.000	+/-	16.271
Y	1.000	+/-	2.214
Sr	40.109	+/-	2.113
Rb	5.349	+/-	4.749
Th	1.000	+/-	156.648
Bi	1.000	+/-	139.076
Au	1.000	+/-	4.790
As	476.895	+/-	27.028
Se	1.000	+/-	3.201
Pb	1574.135	+/-	24.597
Hg	1.000	+/-	2.718
Zn	28.470	+/-	6.738
Cu	481.580	+/-	20.989
Ni	1.000	+/-	21.460
Co	1.000	+/-	71.724
Fe	30834.313	+/-	287.536
Mn	1.000	+/-	46.190
Cr	77.299	+/-	26.655
V	43.602	+/-	26.722
Ti	172.478	+/-	140.807
Ca	103440.109	+/-	694.115
K	3380.780	+/-	193.157
Al	4676.711	+/-	806.568
P	2351.938	+/-	127.576
Si	9634.647	+/-	447.776
Cl	1764.878	+/-	40.035
S	7289.260	+/-	96.940
Mg	1.000	+/-	8943.264