

mRFA -Ergebnisse

XL3t-69288

Reading No 84
 Mode Mining
 Time 2018-04-27 11:22
 Duration 121.15
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags
 INV NR Gm3
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P1 PALMETTMUSTER 2
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	133.193
La	1.000	+/-	61.228
Ba	1.000	+/-	65.413
Sb	46.921	+/-	23.255
Sn	53.496	+/-	15.226
Cd	48.076	+/-	9.681
Ag	567.528	+/-	19.574
Bal	918103.313	+/-	731.150
Nb	37.402	+/-	22.983
Zr	1.000	+/-	76.548
Y	1.000	+/-	18.924
Sr	1.000	+/-	7.362
Rb	1.000	+/-	41.214
Th	1.000	+/-	1112.170
Bi	1.000	+/-	816.445
Au	1.000	+/-	47.370
As	7493.156	+/-	201.819
Se	1.000	+/-	15.231
Pb	32788.988	+/-	527.888
Hg	3333.301	+/-	66.484
Zn	223.388	+/-	24.057
Cu	198.569	+/-	23.286
Ni	1.000	+/-	33.652
Co	1.000	+/-	40.576
Fe	1019.377	+/-	81.403
Mn	118.150	+/-	74.518
Cr	1.000	+/-	33.197
V	1.000	+/-	18.397
Ti	1.000	+/-	86.667
Ca	9359.302	+/-	217.371
K	1076.760	+/-	132.105
Al	464.904	+/-	447.007
P	2312.948	+/-	118.990
Si	3956.889	+/-	278.276
Cl	1593.960	+/-	43.794
S	17203.598	+/-	322.233
Mg	1.000	+/-	4507.780

mRFA -Ergebnisse

XL3t-69288

Reading No 85
 Mode Mining
 Time 2018-04-27 11:27
 Duration 121.10
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags
 INV NR Gm3
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P2 BLATTMETALLMUSTER BETTLER
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	107.059
La	1.000	+/-	48.737
Ba	1.000	+/-	52.261
Sb	1.000	+/-	18.742
Sn	32.189	+/-	10.836
Cd	13.884	+/-	6.970
Ag	217.854	+/-	10.468
Bal	905589.875	+/-	752.409
Nb	38.956	+/-	19.832
Zr	1.000	+/-	66.814
Y	1.000	+/-	16.208
Sr	67.724	+/-	7.029
Rb	1.000	+/-	34.781
Th	1.000	+/-	979.021
Bi	1.000	+/-	726.495
Au	1.000	+/-	40.508
As	6277.130	+/-	175.077
Se	1.000	+/-	12.558
Pb	29004.221	+/-	441.651
Hg	1723.097	+/-	41.044
Zn	174.948	+/-	19.439
Cu	250.598	+/-	23.488
Ni	1.000	+/-	32.610
Co	1.000	+/-	36.862
Fe	919.427	+/-	74.696
Mn	84.249	+/-	69.501
Cr	47.889	+/-	18.657
V	19.281	+/-	15.203
Ti	1.000	+/-	79.371
Ca	32355.453	+/-	529.029
K	978.530	+/-	116.290
Al	674.342	+/-	416.946
P	1136.681	+/-	92.515
Si	4842.309	+/-	273.782
Cl	1574.399	+/-	39.236
S	13976.937	+/-	239.481
Mg	1.000	+/-	4649.087

mRFA -Ergebnisse

XL3t-69288

Reading No 86
 Mode Mining
 Time 2018-04-27 11:31
 Duration 120.51
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags
 INV NR Gm3
 OBJEKT TAFELGEMAELENDE
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P3 HOLZEINSATZ
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	99.862
La	1.000	+/-	45.759
Ba	1.000	+/-	49.054
Sb	1.000	+/-	17.169
Sn	1.000	+/-	11.678
Cd	203.455	+/-	10.975
Ag	1.000	+/-	4.974
Bal	878069.438	+/-	844.399
Nb	1.000	+/-	12.830
Zr	1.000	+/-	36.521
Y	1.000	+/-	8.750
Sr	96.504	+/-	8.256
Rb	1.000	+/-	18.207
Th	1.000	+/-	526.461
Bi	1.000	+/-	433.827
Au	1.000	+/-	47.657
As	3377.191	+/-	97.505
Se	94.611	+/-	67.579
Pb	10049.062	+/-	142.353
Hg	6116.943	+/-	86.769
Zn	797.172	+/-	36.302
Cu	37.954	+/-	16.431
Ni	1.000	+/-	32.676
Co	1.000	+/-	55.606
Fe	8469.557	+/-	197.240
Mn	171.595	+/-	78.113
Cr	329.046	+/-	27.518
V	1.000	+/-	51.999
Ti	1.000	+/-	239.762
Ca	34934.484	+/-	479.442
K	3339.102	+/-	196.639
Al	3544.089	+/-	659.425
P	8390.250	+/-	206.610
Si	16619.945	+/-	544.814
Cl	909.643	+/-	33.088
S	24449.869	+/-	318.128
Mg	1.000	+/-	8712.959

mRFA -Ergebnisse

XL3t-69288

Reading No 87
 Mode Mining
 Time 2018-04-27 11:36
 Duration 121.11
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags
 INV NR Gm3
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P4 BLUETENMUSTER 2
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	103.145
La	1.000	+/-	47.630
Ba	1.000	+/-	50.842
Sb	1.000	+/-	22.091
Sn	52.502	+/-	10.751
Cd	13.634	+/-	6.872
Ag	124.258	+/-	8.267
Bal	929211.750	+/-	565.131
Nb	1.000	+/-	25.246
Zr	1.000	+/-	54.977
Y	1.000	+/-	13.175
Sr	21.381	+/-	7.893
Rb	1.000	+/-	28.285
Th	1.000	+/-	820.855
Bi	1.000	+/-	600.757
Au	1.000	+/-	47.770
As	5388.792	+/-	146.225
Se	1.000	+/-	16.995
Pb	19617.570	+/-	299.800
Hg	5025.833	+/-	83.783
Zn	304.978	+/-	27.415
Cu	110.684	+/-	19.135
Ni	1.000	+/-	31.859
Co	1.000	+/-	31.224
Fe	1299.920	+/-	84.104
Mn	86.906	+/-	69.457
Cr	1.000	+/-	24.162
V	1.000	+/-	19.627
Ti	1.000	+/-	77.022
Ca	20536.859	+/-	359.126
K	745.109	+/-	108.839
Al	1.000	+/-	597.873
P	1745.378	+/-	93.841
Si	2614.442	+/-	218.046
Cl	1409.050	+/-	35.894
S	11690.964	+/-	199.780
Mg	1.000	+/-	4028.127

mRFA -Ergebnisse

XL3t-69288

Reading No 88
 Mode Mining
 Time 2018-04-27 11:41
 Duration 120.75
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags
 INV NR Gm3
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P5 PALMETTMUSTER 1
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	137.199
La	1.000	+/-	62.886
Ba	1.000	+/-	66.963
Sb	35.802	+/-	23.382
Sn	82.162	+/-	15.182
Cd	42.022	+/-	9.613
Ag	362.168	+/-	15.790
Bal	889270.125	+/-	1039.267
Nb	38.284	+/-	26.998
Zr	1.000	+/-	88.816
Y	1.000	+/-	22.335
Sr	103.878	+/-	10.677
Rb	1.000	+/-	49.880
Th	1.000	+/-	1356.881
Bi	1.000	+/-	947.151
Au	1.000	+/-	58.020
As	8771.018	+/-	240.681
Se	1.000	+/-	14.737
Pb	37921.305	+/-	661.012
Hg	3632.106	+/-	77.004
Zn	309.587	+/-	28.369
Cu	80.806	+/-	21.133
Ni	1.000	+/-	56.422
Co	1.000	+/-	53.522
Fe	1202.046	+/-	92.509
Mn	1.000	+/-	122.134
Cr	1.000	+/-	31.779
V	1.000	+/-	19.460
Ti	1.000	+/-	100.486
Ca	25871.027	+/-	504.618
K	1748.995	+/-	159.886
Al	1200.903	+/-	507.838
P	2946.493	+/-	133.506
Si	5278.549	+/-	315.633
Cl	1807.571	+/-	48.574
S	19295.229	+/-	372.042
Mg	1.000	+/-	5542.988

mRFA -Ergebnisse

XL3t-69288

Reading No 89
 Mode Mining
 Time 2018-04-27 11:45
 Duration 121.54
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags
 INV NR Gm3
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P6 KLEID ROT BLAU
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	72.164
La	1.000	+/-	33.042
Ba	1.000	+/-	35.424
Sb	1.000	+/-	13.478
Sn	12.427	+/-	6.712
Cd	17.421	+/-	5.090
Ag	4.558	+/-	3.211
Bal	925993.875	+/-	460.108
Nb	12.344	+/-	9.488
Zr	1.000	+/-	33.966
Y	1.000	+/-	7.787
Sr	125.468	+/-	4.522
Rb	1.000	+/-	21.733
Th	1.000	+/-	492.688
Bi	1.000	+/-	396.710
Au	1.000	+/-	13.004
As	3381.709	+/-	91.578
Se	1.000	+/-	8.520
Pb	12127.401	+/-	151.367
Hg	1.000	+/-	7.103
Zn	1.000	+/-	16.321
Cu	9904.797	+/-	146.812
Ni	1.000	+/-	23.974
Co	182.614	+/-	36.405
Fe	2652.026	+/-	90.440
Mn	1.000	+/-	60.064
Cr	1.000	+/-	17.921
V	1.000	+/-	18.227
Ti	1.000	+/-	74.088
Ca	29668.500	+/-	375.146
K	1268.964	+/-	101.362
Al	811.502	+/-	346.777
P	226.059	+/-	65.729
Si	2592.875	+/-	193.592
Cl	1302.506	+/-	28.931
S	9714.951	+/-	131.815
Mg	1.000	+/-	3706.780

mRFA -Ergebnisse

XL3t-69288

Reading No 90
 Mode Mining
 Time 2018-04-27 11:49
 Duration 120.52
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags
 INV NR Gm3
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P7 BUCH
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	81.859
La	1.000	+/-	37.444
Ba	1.000	+/-	40.210
Sb	1.000	+/-	23.125
Sn	8.359	+/-	7.458
Cd	7.086	+/-	5.430
Ag	5.888	+/-	3.655
Bal	918563.313	+/-	513.434
Nb	16.496	+/-	10.704
Zr	1.000	+/-	37.918
Y	1.000	+/-	8.630
Sr	113.770	+/-	4.518
Rb	1.000	+/-	24.176
Th	1.000	+/-	594.282
Bi	1.000	+/-	426.806
Au	1.000	+/-	14.103
As	3581.910	+/-	100.941
Se	1.000	+/-	9.025
Pb	14527.781	+/-	188.169
Hg	1.000	+/-	7.715
Zn	62.331	+/-	8.851
Cu	862.108	+/-	32.184
Ni	1.000	+/-	24.510
Co	1.000	+/-	20.449
Fe	501.338	+/-	51.189
Mn	1.000	+/-	55.208
Cr	1.000	+/-	20.518
V	1.000	+/-	13.260
Ti	1.000	+/-	62.522
Ca	48268.520	+/-	621.582
K	1460.084	+/-	111.279
Al	1.000	+/-	360.630
P	414.979	+/-	72.478
Si	2021.336	+/-	199.047
Cl	1220.693	+/-	30.929
S	8364.047	+/-	129.286
Mg	1.000	+/-	3949.566

mRFA -Ergebnisse

XL3t-69288

Reading No 91
 Mode Mining
 Time 2018-04-27 11:52
 Duration 121.93
 Units ppm
 Sigma Value 2
 Sequence Final
 Flags
 INV NR Gm3
 OBJEKT TAFELGEMAELEN
 MATERIAL HOLZ METALL FASSUNG
 ANALYSESTELLE P8 NIMBUS
 MESSAUFBAU STATIV
 FILTER m30lo30hi30li30
 User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	75.850
La	1.000	+/-	34.715
Ba	1.000	+/-	37.221
Sb	1.000	+/-	16.562
Sn	11.454	+/-	7.069
Cd	8.052	+/-	5.103
Ag	14.804	+/-	3.748
Bal	937666.938	+/-	403.722
Nb	11.160	+/-	9.716
Zr	1.000	+/-	34.704
Y	1.000	+/-	7.983
Sr	120.558	+/-	5.250
Rb	1.000	+/-	20.916
Th	1.000	+/-	501.568
Bi	1.000	+/-	420.685
Au	110.131	+/-	27.371
As	3674.084	+/-	94.815
Se	1.000	+/-	9.978
Pb	11930.634	+/-	152.897
Hg	1002.114	+/-	23.530
Zn	130.036	+/-	15.500
Cu	3583.713	+/-	72.736
Ni	1.000	+/-	24.114
Co	1.000	+/-	26.492
Fe	1781.549	+/-	79.192
Mn	1.000	+/-	56.014
Cr	1.000	+/-	16.767
V	1.000	+/-	13.865
Ti	1.000	+/-	81.436
Ca	20663.227	+/-	300.527
K	1493.595	+/-	110.183
Al	1.000	+/-	521.096
P	938.486	+/-	79.408
Si	3803.331	+/-	230.533
Cl	1580.293	+/-	34.028
S	11475.931	+/-	164.065
Mg	1.000	+/-	3888.882