

mRFA -Ergebnisse

XL3t-69288

Reading No 1
Mode Mining
Time 2019-12-11 11:25
Duration 121.49
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm37
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P5 HENNIN
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	124.643
La	1.000	+/-	56.767
Ba	1.000	+/-	60.948
Sb	227.906	+/-	24.367
Sn	4361.637	+/-	71.715
Cd	48.826	+/-	9.652
Ag	139.384	+/-	9.561
Bal	888401.188	+/-	870.506
Nb	44.273	+/-	16.018
Zr	1.000	+/-	79.803
Y	1.000	+/-	14.060
Sr	147.257	+/-	6.582
Rb	1.000	+/-	26.035
Th	1.000	+/-	788.128
Bi	1.000	+/-	997.528
Au	1.000	+/-	25.407
As	5259.845	+/-	159.241
Se	26.580	+/-	18.986
Pb	23100.875	+/-	367.092
Hg	1.000	+/-	12.473
Zn	106.896	+/-	12.872
Cu	428.518	+/-	29.438
Ni	1.000	+/-	34.473
Co	1.000	+/-	95.253
Fe	27315.082	+/-	516.313
Mn	364.677	+/-	83.439
Cr	296.395	+/-	28.377
V	1.000	+/-	23.191
Ti	1.000	+/-	120.180
Ca	18386.361	+/-	348.261
K	3210.382	+/-	195.659
Al	1264.557	+/-	534.377
P	1136.269	+/-	109.119
Si	6010.776	+/-	331.415
Cl	1768.664	+/-	45.048
S	17953.689	+/-	305.958
Mg	1.000	+/-	10686.801

mRFA -Ergebnisse

XL3t-69288

Reading No 2
Mode Mining
Time 2019-12-11 11:29
Duration 121.55
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm37
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P6 HENNIN
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	182.725
La	1.000	+/-	83.756
Ba	1.000	+/-	88.413
Sb	61.960	+/-	31.353
Sn	1058.502	+/-	43.143
Cd	17.347	+/-	11.897
Ag	473.802	+/-	23.655
Bal	826375.000	+/-	1936.992
Nb	140.903	+/-	43.909
Zr	1.000	+/-	135.103
Y	1.000	+/-	36.760
Sr	163.968	+/-	11.455
Rb	1.000	+/-	72.107
Th	1.000	+/-	1800.388
Bi	1.000	+/-	1977.115
Au	1.000	+/-	52.992
As	14575.476	+/-	384.732
Se	52.653	+/-	37.609
Pb	69401.992	+/-	1308.017
Hg	1.000	+/-	24.951
Zn	176.223	+/-	17.610
Cu	253.981	+/-	30.538
Ni	1.000	+/-	62.737
Co	1.000	+/-	79.107
Fe	5204.668	+/-	199.675
Mn	200.382	+/-	103.460
Cr	172.673	+/-	42.045
V	1.000	+/-	52.111
Ti	7009.053	+/-	360.435
Ca	8387.775	+/-	254.149
K	667.583	+/-	192.639
Al	4086.355	+/-	874.622
P	4136.574	+/-	205.491
Si	12200.161	+/-	552.480
Cl	3524.205	+/-	92.514
S	41658.781	+/-	867.874
Mg	1.000	+/-	11798.364

mRFA -Ergebnisse

XL3t-69288

Reading No 3
Mode Mining
Time 2019-12-11 11:33
Duration 121.73
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm37
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P7 PILATUS HINTERGRUND
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	100.338
La	1.000	+/-	45.815
Ba	1.000	+/-	49.045
Sb	1.000	+/-	27.503
Sn	3271.016	+/-	49.368
Cd	48.578	+/-	7.905
Ag	143.575	+/-	8.172
Bal	899597.250	+/-	687.917
Nb	19.317	+/-	10.604
Zr	1.000	+/-	47.273
Y	1.000	+/-	9.174
Sr	118.157	+/-	5.185
Rb	1.000	+/-	17.011
Th	1.000	+/-	548.827
Bi	1.000	+/-	628.970
Au	87.046	+/-	23.651
As	3071.113	+/-	103.690
Se	1.000	+/-	16.046
Pb	13053.968	+/-	184.731
Hg	73.852	+/-	13.420
Zn	70.968	+/-	15.618
Cu	7864.500	+/-	142.921
Ni	1.000	+/-	29.555
Co	1.000	+/-	77.899
Fe	22959.730	+/-	375.518
Mn	464.751	+/-	76.732
Cr	65.718	+/-	22.453
V	1.000	+/-	30.362
Ti	1.000	+/-	115.695
Ca	21520.027	+/-	351.772
K	2816.203	+/-	191.503
Al	1468.610	+/-	490.125
P	1092.433	+/-	95.307
Si	8971.775	+/-	368.469
Cl	1249.561	+/-	33.897
S	11971.834	+/-	177.327
Mg	1.000	+/-	4911.221

mRFA -Ergebnisse

XL3t-69288

Reading No 4
Mode Mining
Time 2019-12-11 11:39
Duration 120.61
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm37
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P8 PILATUS HINTERGRUND 2
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	119.846
La	1.000	+/-	54.639
Ba	1.000	+/-	58.378
Sb	68.815	+/-	20.895
Sn	2774.521	+/-	50.141
Cd	31.826	+/-	8.572
Ag	163.762	+/-	9.650
Bal	896637.125	+/-	816.385
Nb	39.346	+/-	16.579
Zr	1.000	+/-	64.197
Y	1.000	+/-	14.196
Sr	120.034	+/-	6.475
Rb	1.000	+/-	26.981
Th	1.000	+/-	811.637
Bi	1.000	+/-	920.362
Au	1.000	+/-	29.709
As	5803.408	+/-	164.963
Se	16.262	+/-	12.765
Pb	23474.500	+/-	372.859
Hg	153.270	+/-	20.157
Zn	164.001	+/-	18.306
Cu	4963.950	+/-	115.150
Ni	1.000	+/-	33.463
Co	1.000	+/-	71.932
Fe	14280.502	+/-	312.379
Mn	268.215	+/-	80.730
Cr	393.707	+/-	25.292
V	1.000	+/-	28.334
Ti	1.000	+/-	136.018
Ca	13863.282	+/-	282.294
K	1724.559	+/-	153.250
Al	1974.951	+/-	499.883
P	1818.633	+/-	114.073
Si	9548.646	+/-	384.238
Cl	1641.120	+/-	41.383
S	20075.471	+/-	344.207
Mg	1.000	+/-	4887.267

mRFA -Ergebnisse

XL3t-69288

Reading No 5
Mode Mining
Time 2019-12-11 11:44
Duration 120.92
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm37
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P9 PILATUS HINTERGRUND 3
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	143.962
La	1.000	+/-	65.850
Ba	1.000	+/-	70.044
Sb	31.241	+/-	23.337
Sn	7961.704	+/-	118.184
Cd	65.840	+/-	11.208
Ag	113.284	+/-	9.257
Bal	885641.250	+/-	934.323
Nb	21.633	+/-	15.434
Zr	1.000	+/-	58.956
Y	1.000	+/-	13.569
Sr	116.011	+/-	7.152
Rb	1.000	+/-	25.088
Th	1.000	+/-	774.356
Bi	1.000	+/-	810.432
Au	1.000	+/-	36.302
As	3739.823	+/-	141.755
Se	1.000	+/-	20.001
Pb	19083.313	+/-	305.156
Hg	1187.142	+/-	33.670
Zn	161.046	+/-	20.595
Cu	2070.828	+/-	66.493
Ni	1.000	+/-	38.154
Co	1.000	+/-	102.205
Fe	28637.404	+/-	525.668
Mn	587.953	+/-	98.190
Cr	188.256	+/-	26.665
V	1.000	+/-	23.260
Ti	1.000	+/-	120.271
Ca	18074.131	+/-	408.105
K	2976.033	+/-	267.083
Al	2553.645	+/-	619.762
P	1552.885	+/-	115.628
Si	10359.969	+/-	436.864
Cl	1340.095	+/-	40.624
S	13536.635	+/-	230.615
Mg	1.000	+/-	5931.458

mRFA -Ergebnisse

XL3t-69288

Reading No 6
Mode Mining
Time 2019-12-11 11:50
Duration 121.94
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm37
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P10 MANTELSCHLIESSE
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	85.864
La	1.000	+/-	39.344
Ba	1.000	+/-	42.073
Sb	1.000	+/-	18.825
Sn	184.798	+/-	12.013
Cd	11.105	+/-	5.766
Ag	358.439	+/-	11.238
Bal	901074.313	+/-	661.333
Nb	31.988	+/-	12.195
Zr	1.000	+/-	46.685
Y	1.000	+/-	10.283
Sr	101.470	+/-	4.959
Rb	1.000	+/-	19.693
Th	1.000	+/-	613.763
Bi	1.000	+/-	656.274
Au	176.792	+/-	27.177
As	4375.534	+/-	121.003
Se	16.729	+/-	11.949
Pb	18026.736	+/-	247.199
Hg	54.286	+/-	14.623
Zn	78.025	+/-	11.912
Cu	1446.727	+/-	44.996
Ni	1.000	+/-	27.631
Co	1.000	+/-	54.253
Fe	10369.895	+/-	221.546
Mn	277.595	+/-	68.861
Cr	32.565	+/-	18.502
V	1.000	+/-	18.564
Ti	1.000	+/-	78.230
Ca	31221.232	+/-	457.538
K	919.928	+/-	123.330
Al	1219.923	+/-	446.954
P	1729.405	+/-	106.689
Si	8898.020	+/-	355.900
Cl	1738.386	+/-	38.891
S	17656.162	+/-	259.388
Mg	1.000	+/-	4761.277

mRFA -Ergebnisse

XL3t-69288

Reading No 8
Mode Mining
Time 2019-12-11 12:00
Duration 121.92
Units ppm
Sigma Value 2
Sequence Final
Flags 3mm
INV NR Gm37
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P11 RESTE BROKAT
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	1.000	+/-	117.543
La	1.000	+/-	95.854
Ba	1.000	+/-	100.875
Sb	1.000	+/-	35.534
Sn	5093.424	+/-	129.680
Cd	72.324	+/-	17.551
Ag	1.000	+/-	12.751
Bal	914086.000	+/-	858.505
Nb	13.913	+/-	12.966
Zr	1.000	+/-	49.483
Y	1.000	+/-	11.183
Sr	116.050	+/-	7.011
Rb	1.000	+/-	21.103
Th	1.000	+/-	652.154
Bi	1.000	+/-	677.367
Au	1.000	+/-	20.711
As	2237.720	+/-	117.034
Se	17.007	+/-	12.793
Pb	10877.917	+/-	211.524
Hg	1.000	+/-	13.430
Zn	71.313	+/-	18.280
Cu	4227.465	+/-	127.472
Ni	1.000	+/-	38.443
Co	1.000	+/-	49.486
Fe	2597.902	+/-	151.154
Mn	1.000	+/-	90.985
Cr	135.592	+/-	29.724
V	1.000	+/-	30.696
Ti	243.490	+/-	139.815
Ca	37135.832	+/-	747.458
K	1256.666	+/-	267.912
Al	1092.913	+/-	566.721
P	186.400	+/-	108.028
Si	8915.961	+/-	500.939
Cl	722.659	+/-	52.589
S	10899.487	+/-	224.779
Mg	1.000	+/-	5273.015

mRFA -Ergebnisse

XL3t-69288

Reading No 9
Mode Mining
Time 2019-12-11 12:04
Duration 120.52
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm37
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P12 AERMEL FUTTER
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	93.104
La	1.000	+/-	42.725
Ba	1.000	+/-	45.738
Sb	1.000	+/-	20.558
Sn	1.000	+/-	11.858
Cd	15.194	+/-	6.516
Ag	390.370	+/-	13.652
Bal	867448.500	+/-	856.559
Nb	30.432	+/-	12.046
Zr	1.000	+/-	44.684
Y	1.000	+/-	10.300
Sr	181.295	+/-	6.061
Rb	1.000	+/-	24.798
Th	1.000	+/-	607.095
Bi	1.000	+/-	664.061
Au	1105.931	+/-	41.329
As	5287.338	+/-	126.506
Se	11.924	+/-	10.946
Pb	17203.951	+/-	236.824
Hg	1.000	+/-	10.626
Zn	93.636	+/-	12.030
Cu	264.083	+/-	21.221
Ni	1.000	+/-	27.195
Co	1.000	+/-	28.015
Fe	1550.495	+/-	79.850
Mn	1.000	+/-	80.209
Cr	47.236	+/-	21.358
V	1.000	+/-	16.198
Ti	1.000	+/-	126.908
Ca	38170.141	+/-	555.579
K	1426.088	+/-	149.214
Al	3325.469	+/-	710.275
P	4926.580	+/-	188.773
Si	21705.594	+/-	647.059
Cl	2632.826	+/-	57.676
S	34182.852	+/-	489.273
Mg	1.000	+/-	10594.029

mRFA -Ergebnisse

XL3t-69288

Reading No 10
Mode Mining
Time 2019-12-11 12:09
Duration 120.19
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm37
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P13 MANTEL
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	77.219
La	1.000	+/-	35.366
Ba	1.000	+/-	38.119
Sb	1.000	+/-	14.242
Sn	54.850	+/-	8.233
Cd	10.328	+/-	5.306
Ag	56.796	+/-	5.051
Bal	825748.313	+/-	907.858
Nb	13.314	+/-	7.313
Zr	1.000	+/-	26.397
Y	1.000	+/-	5.990
Sr	153.056	+/-	4.555
Rb	1.000	+/-	11.492
Th	1.000	+/-	389.979
Bi	1.000	+/-	396.157
Au	45.822	+/-	15.401
As	2155.177	+/-	71.413
Se	1.000	+/-	10.891
Pb	8995.154	+/-	104.933
Hg	1.000	+/-	6.597
Zn	22.993	+/-	7.048
Cu	184.857	+/-	16.745
Ni	1.000	+/-	23.264
Co	1.000	+/-	34.493
Fe	4675.898	+/-	118.795
Mn	1.000	+/-	54.590
Cr	28.405	+/-	17.430
V	1.000	+/-	16.862
Ti	1.000	+/-	90.460
Ca	134096.359	+/-	1144.958
K	896.996	+/-	126.927
Al	1808.185	+/-	720.585
P	433.394	+/-	112.683
Si	8916.899	+/-	442.305
Cl	995.030	+/-	33.610
S	10708.224	+/-	141.307
Mg	1.000	+/-	9609.422

mRFA -Ergebnisse

XL3t-69288

Reading No 12
Mode Mining
Time 2019-12-11 12:17
Duration 120.17
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm37
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P14 MANTEL
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	66.820
La	1.000	+/-	30.747
Ba	1.000	+/-	33.019
Sb	1.000	+/-	12.017
Sn	1.000	+/-	8.925
Cd	15.182	+/-	4.789
Ag	3.109	+/-	3.012
Bal	837893.750	+/-	801.603
Nb	1.000	+/-	4.082
Zr	1.000	+/-	16.770
Y	1.000	+/-	3.712
Sr	159.830	+/-	4.131
Rb	1.000	+/-	7.482
Th	1.000	+/-	249.948
Bi	1.000	+/-	227.221
Au	1.000	+/-	6.924
As	980.035	+/-	44.343
Se	1.000	+/-	6.611
Pb	4069.669	+/-	49.045
Hg	1.000	+/-	3.459
Zn	18.107	+/-	6.682
Cu	854.777	+/-	27.892
Ni	1.000	+/-	21.464
Co	1.000	+/-	45.782
Fe	11360.793	+/-	176.084
Mn	57.530	+/-	53.692
Cr	45.967	+/-	17.434
V	1.000	+/-	26.136
Ti	236.116	+/-	96.393
Ca	101876.375	+/-	762.987
K	1428.828	+/-	123.515
Al	2693.365	+/-	650.560
P	520.659	+/-	105.572
Si	25005.379	+/-	629.296
Cl	1161.625	+/-	32.211
S	11618.910	+/-	131.722
Mg	1.000	+/-	6979.071

mRFA -Ergebnisse

XL3t-69288

Reading No 13
Mode Mining
Time 2019-12-11 12:23
Duration 120.74
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm37
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P15 SCHERGE
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	-339.000	+/-	119.334
La	1.000	+/-	54.989
Ba	1.000	+/-	58.506
Sb	1.000	+/-	30.959
Sn	1366.680	+/-	32.124
Cd	18.248	+/-	8.039
Ag	343.933	+/-	13.309
Bal	912428.375	+/-	687.162
Nb	34.084	+/-	17.179
Zr	1.000	+/-	58.887
Y	1.000	+/-	14.536
Sr	92.932	+/-	5.689
Rb	1.000	+/-	28.408
Th	1.000	+/-	829.648
Bi	1.000	+/-	835.792
Au	356.879	+/-	35.549
As	5468.010	+/-	159.541
Se	1.000	+/-	13.442
Pb	24923.141	+/-	382.531
Hg	1.000	+/-	15.303
Zn	111.096	+/-	14.897
Cu	2719.659	+/-	73.477
Ni	1.000	+/-	31.831
Co	1.000	+/-	48.278
Fe	5835.394	+/-	172.136
Mn	82.222	+/-	70.784
Cr	45.908	+/-	20.932
V	1.000	+/-	24.125
Ti	131.885	+/-	105.125
Ca	15593.925	+/-	308.265
K	2951.852	+/-	178.155
Al	1041.329	+/-	436.890
P	1653.569	+/-	101.578
Si	8855.020	+/-	361.838
Cl	1533.458	+/-	39.571
S	14412.373	+/-	253.559
Mg	1.000	+/-	4597.359

mRFA -Ergebnisse

XL3t-69288

Reading No 14
Mode Mining
Time 2019-12-11 12:27
Duration 121.71
Units ppm
Sigma Value 2
Sequence Final
Flags 3mm
INV NR Gm37
OBJEKT TAFELGEMAELENDE
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P16 HENNIN
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	1.000	+/-	209.377
La	1.000	+/-	238.132
Ba	1.000	+/-	261.934
Sb	1.000	+/-	100.964
Sn	74.840	+/-	48.720
Cd	32.459	+/-	25.108
Ag	253.985	+/-	36.669
Bal	830245.063	+/-	2736.489
Nb	122.566	+/-	66.151
Zr	1.000	+/-	198.285
Y	1.000	+/-	54.222
Sr	181.785	+/-	17.269
Rb	1.000	+/-	109.863
Th	1.000	+/-	2532.615
Bi	1.000	+/-	2208.861
Au	1.000	+/-	80.379
As	15157.042	+/-	509.932
Se	61.248	+/-	43.748
Pb	77280.641	+/-	1938.298
Hg	1.000	+/-	38.673
Zn	161.471	+/-	22.687
Cu	222.931	+/-	39.149
Ni	1.000	+/-	95.636
Co	78.329	+/-	56.261
Fe	349.750	+/-	109.312
Mn	170.077	+/-	136.954
Cr	1.000	+/-	66.781
V	1.000	+/-	56.066
Ti	3366.502	+/-	330.940
Ca	3596.780	+/-	212.984
K	467.639	+/-	226.948
Al	2439.001	+/-	996.737
P	4769.749	+/-	279.752
Si	11480.725	+/-	723.055
Cl	6030.625	+/-	200.574
S	43456.801	+/-	1154.055
Mg	1.000	+/-	16083.503

mRFA -Ergebnisse

XL3t-69288

Reading No 15
Mode Mining
Time 2019-12-11 12:33
Duration 121.01
Units ppm
Sigma Value 2
Sequence Final
Flags 3mm
INV NR Gm37
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P17 HENNIN
MESSAUFBAU STATIV
FILTER m30lo30hi30li30
User Login Raquet



Ele	ppm	+/-	$\pm 2\sigma$
Ce	1.000	+/-	124.717
La	1.000	+/-	101.548
Ba	1.000	+/-	107.000
Sb	156.872	+/-	41.898
Sn	3186.225	+/-	101.796
Cd	32.438	+/-	16.214
Ag	215.844	+/-	20.164
Bal	879271.375	+/-	1212.200
Nb	1.000	+/-	18.941
Zr	1.000	+/-	55.725
Y	1.000	+/-	13.706
Sr	144.181	+/-	8.371
Rb	1.000	+/-	26.261
Th	1.000	+/-	773.454
Bi	1.000	+/-	753.765
Au	211.404	+/-	39.249
As	2877.406	+/-	138.777
Se	1.000	+/-	19.867
Pb	13096.944	+/-	256.316
Hg	1.000	+/-	14.977
Zn	126.239	+/-	39.662
Cu	42776.680	+/-	723.462
Ni	1.000	+/-	40.081
Co	1.000	+/-	73.799
Fe	7683.085	+/-	236.224
Mn	92.182	+/-	89.515
Cr	165.780	+/-	28.392
V	1.000	+/-	25.058
Ti	1.000	+/-	162.556
Ca	21128.773	+/-	406.155
K	1488.222	+/-	168.446
Al	1666.588	+/-	578.733
P	1099.155	+/-	117.506
Si	7015.128	+/-	414.822
Cl	2608.026	+/-	70.820
S	14957.459	+/-	258.816
Mg	1.000	+/-	6303.195