

mRFA -Ergebnisse

XL3t-69288

Reading No 17  
Mode Mining  
Time 2019-06-27 11:53  
Duration 122.06  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags 3mm  
INV NR Gm61  
OBJEKT GEMAELENDE  
MATERIAL TEXTIL FASSUNG  
ANALYSESTELLE P1 UNTERZEICHNUNG  
MESSAUFBAU STATIV  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	117.339
La	1.000	+/-	95.550
Ba	1.000	+/-	100.807
Sb	47.064	+/-	36.590
Sn	471.749	+/-	39.794
Cd	15.734	+/-	13.788
Ag	1.000	+/-	13.011
Bal	892538.000	+/-	1054.366
Nb	32.259	+/-	22.600
Zr	1.000	+/-	76.339
Y	1.000	+/-	18.911
Sr	73.490	+/-	6.622
Rb	1.000	+/-	47.568
Th	1.000	+/-	1076.528
Bi	1.000	+/-	858.978
Au	1.000	+/-	27.963
As	5747.013	+/-	193.060
Se	1.000	+/-	19.792
Pb	27676.146	+/-	509.676
Hg	1.000	+/-	16.232
Zn	2553.613	+/-	78.160
Cu	89.021	+/-	21.670
Ni	1.000	+/-	35.848
Co	1.000	+/-	59.001
Fe	511.012	+/-	79.667
Mn	112.881	+/-	89.889
Cr	57.452	+/-	24.719
V	1.000	+/-	21.901
Ti	1.000	+/-	84.749
Ca	9875.501	+/-	269.638
K	300.341	+/-	115.985
Al	2578.674	+/-	632.792
P	1908.818	+/-	157.981
Si	10574.249	+/-	530.252
Cl	4960.263	+/-	126.039
S	28652.389	+/-	579.558
Mg	11224.340	+/-	6988.697

mRFA -Ergebnisse

XL3t-69288

Reading No 18  
Mode Mining  
Time 2019-06-27 11:58  
Duration 120.69  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags 3mm  
INV NR Gm61  
OBJEKT GEMAELENDE  
MATERIAL TEXTIL FASSUNG  
ANALYSESTELLE P2 UNTERZEICHNUNG  
MESSAUFBAU STATIV  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	176.270
La	1.000	+/-	138.685
Ba	1.000	+/-	139.676
Sb	129.909	+/-	56.328
Sn	1044.470	+/-	83.751
Cd	1.000	+/-	32.598
Ag	1.000	+/-	18.693
Bal	816410.125	+/-	2470.136
Nb	56.228	+/-	47.771
Zr	1.000	+/-	149.801
Y	1.000	+/-	39.387
Sr	118.792	+/-	12.403
Rb	1.000	+/-	105.232
Th	1.000	+/-	2438.237
Bi	1.000	+/-	1627.748
Au	1.000	+/-	51.758
As	10863.473	+/-	398.827
Se	1.000	+/-	32.244
Pb	54360.566	+/-	1368.501
Hg	1.000	+/-	30.009
Zn	207.547	+/-	23.662
Cu	113.408	+/-	30.141
Ni	1.000	+/-	49.688
Co	1.000	+/-	70.763
Fe	358.370	+/-	98.458
Mn	1.000	+/-	167.849
Cr	1.000	+/-	42.300
V	1.000	+/-	29.678
Ti	1.000	+/-	139.259
Ca	15754.826	+/-	522.158
K	1.000	+/-	309.322
Al	3941.194	+/-	1123.029
P	3348.704	+/-	266.695
Si	16763.320	+/-	885.805
Cl	7784.303	+/-	257.901
S	50008.270	+/-	1392.835
Mg	18736.564	+/-	12240.340

mRFA -Ergebnisse

XL3t-69288

Reading No 19  
Mode Mining  
Time 2019-06-27 12:02  
Duration 121.77  
Units ppm  
Sigma Value 2  
Sequence Final  
Flags 3mm  
INV NR Gm61  
OBJEKT GEMAELENDE  
MATERIAL TEXTIL FASSUNG  
ANALYSESTELLE P3 RETUSCHE  
MESSAUFBAU STATIV  
FILTER m30lo30hi30li30  
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	150.571
La	1.000	+/-	123.326
Ba	1.000	+/-	129.045
Sb	1.000	+/-	44.782
Sn	604.113	+/-	57.468
Cd	23.226	+/-	18.660
Ag	1.000	+/-	12.730
Bal	860759.438	+/-	1796.722
Nb	1.000	+/-	46.621
Zr	1.000	+/-	101.659
Y	1.000	+/-	25.571
Sr	140.309	+/-	11.092
Rb	1.000	+/-	52.514
Th	1.000	+/-	1381.672
Bi	1.000	+/-	1228.112
Au	1.000	+/-	40.825
As	5213.726	+/-	245.231
Se	1.000	+/-	30.710
Pb	27581.029	+/-	641.776
Hg	1.000	+/-	26.091
Zn	54312.797	+/-	1083.022
Cu	2387.631	+/-	96.099
Ni	1.000	+/-	46.275
Co	1832.802	+/-	127.439
Fe	6258.600	+/-	237.480
Mn	1218.060	+/-	150.246
Cr	1641.079	+/-	58.980
V	1.000	+/-	50.597
Ti	1.000	+/-	246.435
Ca	17666.477	+/-	422.732
K	472.964	+/-	148.039
Al	7952.422	+/-	918.467
P	238.424	+/-	80.970
Si	4700.582	+/-	374.482
Cl	1814.966	+/-	66.038
S	5181.358	+/-	132.987
Mg	1.000	+/-	3663.355