

Certificate of Verification

XL3t-69288

Reading No 1
Mode Mining
Time 2017-01-18 16:30
Duration 122.19
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1065
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P1 HINTERGRUND
MESSAUFBAU STATIV ANLIEGEND
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	1488.858	+/-	410.775
La	712.567	+/-	184.024
Ba	695.402	+/-	192.569
Sb	1.000	+/-	73.785
Sn	448.272	+/-	46.541
Cd	1.000	+/-	23.885
Ag	18.040	+/-	14.977
Bal	697292.000	+/-	5912.026
Nb	285.738	+/-	124.567
Zr	1.000	+/-	342.962
Y	1.000	+/-	95.607
Sr	40.898	+/-	20.983
Rb	1.000	+/-	202.193
Th	1.000	+/-	5716.381
Bi	1.000	+/-	3210.939
Au	1.000	+/-	103.650
As	23628.879	+/-	795.797
Se	71.787	+/-	51.277
Pb	177962.406	+/-	4691.232
Hg	1.000	+/-	51.333
Zn	157.822	+/-	23.461
Cu	297.659	+/-	44.169
Ni	238.706	+/-	72.549
Co	170.354	+/-	63.033
Fe	1189.517	+/-	138.398
Mn	246.751	+/-	132.712
Cr	89.289	+/-	43.439
V	1.000	+/-	43.553
Ti	1.000	+/-	193.395
Ca	4683.454	+/-	225.685
K	453.857	+/-	196.722
Al	3003.347	+/-	1085.555
P	2873.361	+/-	201.765
Si	11963.365	+/-	591.280
Cl	3429.543	+/-	120.023
S	47372.871	+/-	1340.395
Mg	20845.180	+/-	12220.927

Supervised By: _____

Certificate of Verification

XL3t-69288

Reading No 2
Mode Mining
Time 2017-01-18 16:34
Duration 122.95
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1065
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P2 HINTERGRUND
MESSAUFBAU STATIV ANLIEGEND
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	361.627
La	188.324	+/-	113.544
Ba	217.651	+/-	120.135
Sb	1.000	+/-	37.569
Sn	306.773	+/-	28.858
Cd	1.000	+/-	13.865
Ag	21.320	+/-	10.229
Bal	764934.938	+/-	3130.238
Nb	152.191	+/-	64.567
Zr	1.000	+/-	190.946
Y	1.000	+/-	51.780
Sr	247.569	+/-	16.744
Rb	1.000	+/-	106.112
Th	1.000	+/-	2496.222
Bi	1.000	+/-	1920.076
Au	963.192	+/-	88.202
As	16578.875	+/-	474.978
Se	42.417	+/-	30.298
Pb	95702.953	+/-	1941.644
Hg	1.000	+/-	32.118
Zn	139.399	+/-	19.799
Cu	395.677	+/-	39.169
Ni	82.749	+/-	54.033
Co	86.372	+/-	54.911
Fe	2135.166	+/-	142.120
Mn	293.993	+/-	110.682
Cr	51.447	+/-	33.676
V	1.000	+/-	47.185
Ti	1.000	+/-	161.836
Ca	31097.102	+/-	661.129
K	705.629	+/-	168.731
Al	3360.535	+/-	892.943
P	3768.004	+/-	189.040
Si	12519.999	+/-	532.454
Cl	2862.275	+/-	78.679
S	40036.734	+/-	826.833
Mg	23108.828	+/-	9878.065

Supervised By: _____

Certificate of Verification

XL3t-69288

Reading No 3
Mode Mining
Time 2017-01-18 16:38
Duration 121.37
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1065
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P3 HINTERGRUND NEU
MESSAUFBAU STATIV ANLIEGEND
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	101.828
La	1.000	+/-	46.821
Ba	1.000	+/-	50.295
Sb	105.847	+/-	19.435
Sn	10.623	+/-	9.390
Cd	11.348	+/-	6.917
Ag	14.970	+/-	4.940
Bal	808424.500	+/-	1060.446
Nb	1.000	+/-	3.666
Zr	1.000	+/-	15.345
Y	1.000	+/-	3.454
Sr	481.073	+/-	8.423
Rb	29.501	+/-	7.929
Th	1.000	+/-	214.666
Bi	1.000	+/-	190.896
Au	3959.344	+/-	64.332
As	354.804	+/-	32.757
Se	1.000	+/-	8.125
Pb	1836.645	+/-	31.986
Hg	1.000	+/-	5.936
Zn	155.204	+/-	16.694
Cu	180.513	+/-	18.495
Ni	1.000	+/-	28.731
Co	1.000	+/-	65.898
Fe	19069.109	+/-	254.967
Mn	1.000	+/-	112.896
Cr	174.463	+/-	30.802
V	63.559	+/-	36.684
Ti	2617.216	+/-	216.870
Ca	76478.625	+/-	643.221
K	6439.011	+/-	230.073
Al	6289.351	+/-	922.368
P	31708.576	+/-	383.047
Si	28216.400	+/-	767.121
Cl	1466.790	+/-	41.768
S	11912.538	+/-	141.362
Mg	1.000	+/-	7700.638

Supervised By: _____

Certificate of Verification

XL3t-69288

Reading No 4
Mode Mining
Time 2017-01-18 16:42
Duration 121.85
Units ppm
Sigma Value 2
Sequence Final
Flags 3mm
INV NR Gm1065
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P4 NIMBUS
MESSAUFBAU STATIV ANLIEGEND
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	1.000	+/-	330.555
La	1.000	+/-	268.577
Ba	213.239	+/-	186.845
Sb	113.199	+/-	66.491
Sn	51.216	+/-	41.525
Cd	1.000	+/-	38.373
Ag	1.000	+/-	18.811
Bal	838734.375	+/-	2292.554
Nb	96.127	+/-	56.707
Zr	1.000	+/-	172.242
Y	1.000	+/-	46.277
Sr	257.723	+/-	17.622
Rb	1.000	+/-	95.103
Th	1.000	+/-	2212.987
Bi	1.000	+/-	1948.767
Au	1.000	+/-	60.113
As	13937.217	+/-	438.232
Se	57.858	+/-	41.327
Pb	70323.742	+/-	1610.461
Hg	1.000	+/-	37.608
Zn	142.309	+/-	19.521
Cu	127.051	+/-	30.690
Ni	83.776	+/-	54.342
Co	84.502	+/-	62.496
Fe	1723.236	+/-	152.088
Mn	185.932	+/-	121.007
Cr	1.000	+/-	44.252
V	1.000	+/-	48.575
Ti	1.000	+/-	188.538
Ca	4415.715	+/-	210.282
K	372.352	+/-	168.621
Al	3810.126	+/-	946.808
P	3242.900	+/-	231.513
Si	15069.489	+/-	759.423
Cl	4158.954	+/-	138.238
S	42798.918	+/-	1058.151
Mg	1.000	+/-	16317.858

Supervised By: _____

Certificate of Verification

XL3t-69288

Reading No 5
Mode Mining
Time 2017-01-18 16:48
Duration 121.24
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm1065
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P5 ROTLACK
MESSAUFBAU STATIV ANLIEGEND
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	148.988
La	1.000	+/-	95.924
Ba	1.000	+/-	118.342
Sb	1.000	+/-	23.525
Sn	34.124	+/-	13.257
Cd	1.000	+/-	8.081
Ag	1.000	+/-	5.086
Bal	829135.750	+/-	1507.282
Nb	66.633	+/-	29.033
Zr	1.000	+/-	93.736
Y	1.000	+/-	24.163
Sr	303.006	+/-	11.597
Rb	1.000	+/-	47.821
Th	1.000	+/-	1294.893
Bi	1.000	+/-	1271.935
Au	1.000	+/-	33.189
As	10125.538	+/-	263.773
Se	15.187	+/-	14.948
Pb	45074.492	+/-	764.602
Hg	1.000	+/-	20.010
Zn	132.031	+/-	14.575
Cu	997.896	+/-	45.516
Ni	1.000	+/-	60.365
Co	1.000	+/-	45.128
Fe	917.689	+/-	83.621
Mn	490.770	+/-	94.194
Cr	1.000	+/-	26.070
V	1.000	+/-	27.035
Ti	1.000	+/-	102.933
Ca	35384.250	+/-	650.314
K	7123.650	+/-	270.776
Al	3707.016	+/-	750.479
P	1142.418	+/-	124.978
Si	33850.438	+/-	902.434
Cl	3081.860	+/-	73.454
S	17645.754	+/-	340.115
Mg	10771.578	+/-	7368.429

Supervised By: _____