

Certificate of Verification

XL3t-69288

Reading No 1
Mode Mining
Time 2016-04-20 14:59
Duration 120.46
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm884
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P1 BUCHSTABE
MESSAUFBAU STATIV ANLIEGEND
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	125.834
La	1.000	+/-	57.573
Ba	1.000	+/-	61.372
Sb	42.010	+/-	21.575
Sn	2912.244	+/-	59.854
Cd	31.739	+/-	9.143
Ag	88.575	+/-	8.403
Bal	881814.563	+/-	1105.626
Nb	1.000	+/-	35.783
Zr	1.000	+/-	75.724
Y	1.000	+/-	19.336
Sr	11.410	+/-	5.348
Rb	73.261	+/-	39.323
Th	1.000	+/-	1047.563
Bi	1.000	+/-	806.624
Au	15302.777	+/-	266.703
As	6232.014	+/-	185.216
Se	1.000	+/-	23.661
Pb	27207.398	+/-	449.390
Hg	1.000	+/-	21.056
Zn	188.769	+/-	35.569
Cu	21427.713	+/-	337.998
Ni	1.000	+/-	36.754
Co	1.000	+/-	35.127
Fe	429.143	+/-	62.339
Mn	1.000	+/-	99.078
Cr	57.543	+/-	21.870
V	1.000	+/-	17.690
Ti	1.000	+/-	91.707
Ca	9165.399	+/-	214.921
K	961.460	+/-	132.019
Al	1.000	+/-	456.695
P	22482.166	+/-	383.136
Si	625.937	+/-	261.487
Cl	1761.088	+/-	40.629
S	9184.766	+/-	156.044
Mg	1.000	+/-	4438.981

Supervised By: _____

Certificate of Verification

XL3t-69288

Reading No 2
Mode Mining
Time 2016-04-20 15:04
Duration 120.95
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm884
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P2 HINTERGRUND GRUEN
MESSAUFBAU STATIV ANLIEGEND
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	104.415
La	1.000	+/-	47.913
Ba	1.000	+/-	50.880
Sb	1.000	+/-	20.587
Sn	2703.679	+/-	49.495
Cd	58.639	+/-	8.462
Ag	11.924	+/-	4.740
Bal	911222.125	+/-	757.019
Nb	51.293	+/-	21.044
Zr	1.000	+/-	70.946
Y	1.000	+/-	17.723
Sr	8.100	+/-	4.325
Rb	1.000	+/-	34.673
Th	1.000	+/-	988.675
Bi	1.000	+/-	932.901
Au	1.000	+/-	23.841
As	6148.673	+/-	185.823
Se	14.334	+/-	13.873
Pb	31754.482	+/-	498.436
Hg	1.000	+/-	14.774
Zn	113.434	+/-	21.453
Cu	18071.178	+/-	308.695
Ni	1.000	+/-	32.658
Co	1.000	+/-	31.008
Fe	596.610	+/-	62.771
Mn	1.000	+/-	65.153
Cr	322.183	+/-	23.483
V	1.000	+/-	27.351
Ti	1.000	+/-	141.578
Ca	9303.128	+/-	228.401
K	1513.918	+/-	152.283
Al	2402.863	+/-	408.625
P	358.588	+/-	64.708
Si	4559.456	+/-	235.864
Cl	1582.528	+/-	37.109
S	9202.879	+/-	163.733
Mg	1.000	+/-	3107.667

Supervised By: _____

Certificate of Verification

XL3t-69288

Reading No 3
Mode Mining
Time 2016-04-20 15:10
Duration 121.19
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm884
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P3 HINTERGRUND GRUEN RETUSCHE
MESSAUFBAU STATIV ANLIEGEND
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	69.560
La	1.000	+/-	31.912
Ba	1.000	+/-	35.160
Sb	14.483	+/-	13.247
Sn	523.380	+/-	14.882
Cd	166.399	+/-	8.433
Ag	12.108	+/-	3.540
Bal	926630.688	+/-	438.333
Nb	22.297	+/-	7.387
Zr	1.000	+/-	33.901
Y	1.000	+/-	5.949
Sr	14.380	+/-	2.215
Rb	1.000	+/-	14.840
Th	1.000	+/-	386.722
Bi	1.000	+/-	414.617
Au	1.000	+/-	9.973
As	1776.300	+/-	68.610
Se	1.000	+/-	9.300
Pb	8511.436	+/-	104.617
Hg	1.000	+/-	6.926
Zn	3289.684	+/-	57.797
Cu	7553.107	+/-	114.141
Ni	1.000	+/-	22.219
Co	1.000	+/-	32.687
Fe	4419.787	+/-	112.498
Mn	1.000	+/-	73.737
Cr	5070.716	+/-	70.015
V	1.000	+/-	68.660
Ti	1.000	+/-	532.925
Ca	15560.530	+/-	243.189
K	3262.486	+/-	176.665
Al	6627.302	+/-	545.821
P	90.533	+/-	62.887
Si	7852.383	+/-	309.032
Cl	1476.378	+/-	32.393
S	7125.569	+/-	103.204
Mg	1.000	+/-	3830.233

Supervised By: _____

Certificate of Verification

XL3t-69288

Reading No 4
Mode Mining
Time 2016-04-20 15:13
Duration 122.05
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm884
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P4 RING
MESSAUFBAU STATIV ANLIEGEND
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	114.034
La	1.000	+/-	52.030
Ba	1.000	+/-	55.664
Sb	1.000	+/-	30.355
Sn	102.171	+/-	12.348
Cd	10.737	+/-	7.302
Ag	19.813	+/-	5.428
Bal	885787.000	+/-	969.211
Nb	60.473	+/-	24.833
Zr	1.000	+/-	81.310
Y	1.000	+/-	20.601
Sr	6.268	+/-	5.701
Rb	1.000	+/-	50.325
Th	1.000	+/-	1118.302
Bi	1.000	+/-	919.148
Au	2354.457	+/-	75.331
As	8631.070	+/-	217.703
Se	1.000	+/-	20.402
Pb	39251.035	+/-	607.946
Hg	226.094	+/-	26.231
Zn	191.207	+/-	19.602
Cu	106.104	+/-	19.625
Ni	1.000	+/-	33.991
Co	1.000	+/-	50.372
Fe	5948.678	+/-	177.582
Mn	1.000	+/-	88.158
Cr	34.221	+/-	22.989
V	1.000	+/-	20.438
Ti	161.378	+/-	112.112
Ca	10785.550	+/-	243.658
K	1964.483	+/-	153.893
Al	3194.054	+/-	496.365
P	7489.188	+/-	183.758
Si	14233.603	+/-	453.713
Cl	2171.363	+/-	48.506
S	17271.180	+/-	298.881
Mg	1.000	+/-	4734.035

Supervised By: _____

Certificate of Verification

XL3t-69288

Reading No 5
Mode Mining
Time 2016-04-20 15:18
Duration 120.04
Units ppm
Sigma Value 2
Sequence Final
Flags
INV NR Gm884
OBJEKT TAFELGEMAELEN
MATERIAL HOLZ METALL FASSUNG
ANALYSESTELLE P5 BUCHSTABE
MESSAUFBAU STATIV ANLIEGEND
FILTER m30lo30hi30li30
User Login Raquet



	ppm	+/-	Error
Ce	-339.000	+/-	103.273
La	1.000	+/-	47.305
Ba	1.000	+/-	50.305
Sb	1.000	+/-	25.336
Sn	2063.822	+/-	40.497
Cd	38.130	+/-	7.855
Ag	48.236	+/-	6.059
Bal	902545.938	+/-	777.880
Nb	32.343	+/-	17.517
Zr	1.000	+/-	60.416
Y	1.000	+/-	14.872
Sr	14.262	+/-	4.143
Rb	32.564	+/-	30.153
Th	1.000	+/-	846.678
Bi	1.000	+/-	794.114
Au	7210.881	+/-	136.250
As	5540.702	+/-	156.358
Se	1.000	+/-	16.671
Pb	23239.268	+/-	351.653
Hg	1.000	+/-	15.470
Zn	158.268	+/-	26.577
Cu	16991.043	+/-	271.168
Ni	1.000	+/-	30.626
Co	1.000	+/-	24.928
Fe	119.054	+/-	45.919
Mn	1.000	+/-	61.721
Cr	56.183	+/-	18.127
V	1.000	+/-	13.803
Ti	1.000	+/-	72.772
Ca	8116.464	+/-	192.343
K	649.221	+/-	116.413
Al	973.387	+/-	396.761
P	17677.604	+/-	309.755
Si	1486.531	+/-	245.023
Cl	1758.606	+/-	38.609
S	11247.531	+/-	182.766
Mg	1.000	+/-	4460.497

Supervised By: _____